

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problems Mailbox.**









14

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : G03F 7/031, C07C 381/00, 309/66, 309/73, C07D 307/54	A1	(11) International Publication Number: WO 00/52530 (43) International Publication Date: 8 September 2000 (08.09.00)
(21) International Application Number: PCT/EP00/01404 (22) International Filing Date: 21 February 2000 (21.02.00) (30) Priority Data: 99810180.2 3 March 1999 (03.03.99) EP (71) Applicant (for all designated States except US): CIBA SPECIALTY CHEMICALS HOLDING INC. [CH/CH]; Klybeckstrasse 141, CH-4057 Basel (CH). (72) Inventors; and (75) Inventors/Applicants (for US only): KURA, Hisatoshi [JP/JP]; 5-3-15-205, Obayashi, Takarazuka, Hyogo 665-0034 (JP). YAMATO, Hitoshi [JP/JP]; 5-2-22-201 Nakayamasatsukidai, Takarazuka, Hyogo 665-0871 (JP). OHWA, Masaki [JP/JP]; 1-1-4, Kotoku-cho, Nada-ku, Kobe City 657-0025 (JP). DIETLIKER, Kurt [CH/CH]; Baselmattweg 132, CH-4123 Allschwil (CH). (74) Common Representative: CIBA SPECIALTY CHEMICALS HOLDING INC.; Patentabteilung, Klybeckstrasse 141, CH-4057 Basel (CH).	(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	

(54) Title: OXIME DERIVATIVES AND THE USE THEREOF AS PHOTOINITIATORS



(57) Abstract

Radically photopolymerizable compositions comprising (a) at least one ethylenically unsaturated photopolymerizable compound; (b) as photoinitiator, at least one compound of formulae (I, II, III, IV, V and/or VI), wherein m is 0 or 1; n is 0, 1, 2 or 3; x is 1 or 2; R₁ is inter alia phenyl, naphthyl, anthracenyl or phenanthryl, a heteroaryl radical, C₂-C₁₂alkenyl, C₄-C₈cycloalkenyl, or C₆-C₁₂bicycloalkenyl; R'₁ is inter alia C₂-C₁₂alkylene, or phenylene; R₂ has one of the meanings of R₁ or inter alia is phenyl; y is 1 or 2; R₃ if x is 1 inter alia is C₁-C₁₈alkylsulfonyl, or phenyl-C₁-C₃alkylsulfonyl, R₃ if x is 2, is for example C₂-C₁₂alkylenedisulfonyl; R₄ and R₅ inter alia are hydrogen, halogen, or C₁-C₈alkyl; R₆, R₇, R₈ inter alia are hydrogen, R₂₆Y-, or phenyl; R₉ inter alia is C₃-C₈cycloalkyl, or phenyl; A is for example -S-, -O-, or -NR₁₀-; Q is C₁-C₈-alkylene optionally interrupted by -O-; X is -O- or -NR₉-; R₁₀ inter alia is hydrogen, or phenyl; and (c) at least one coinitiator; are especially suitable for the preparation of colour filter systems.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Oxime derivatives and the use thereof as photoinitiators

The invention relates to oxime derivatives and their use as photoinitiators in radically photopolymerizable compositions.

Oxime sulfonates are known as photoacid generators and accordingly are used in acid-curable compositions and in chemically amplified resists. In US 4540598 surface-coating compositions based on photosensitive oxime sulfonates as photolabile acids and customary acid-curable resins are disclosed. In EP 571330 the use of α -(4-toluene-sulfonyloxyimino)-4-methoxybenzyl cyanide and α -(4-toluene-sulfonyloxyimino)-3-thienylmethyl cyanide as latent acid donors in positive and negative photoresists for wavelengths of 340-390 nm, especially those in the radiation region of the mercury i line (365 nm) is described. In GB 2306958 the use of oxime-sulfonates as latent acid donors in positive and negative photoresists for wavelengths between 180 and 600 nm, especially those in the radiation region beyond 390 nm is reported. In US 5714625 non-aromatic α -(alkylsulfonyloxyimino)-1-cyclohexenylacetonitriles and α -(alkylsulfonyloxyimino)-1-cyclopentenylacetonitriles are disclosed.

It is known that certain oxime carboxylate ester derivatives are photoinitiators as described in US patent 3558309. Further disclosure of oxime carboxylate ester compounds is given for example in US 4255513, US 4590145, US 4202697, Chemical Abstract No. 96:52526c, J. Chem. Eng. Data 9(3), 403-4 (1964), J. Chin. Chem. Soc. (Taipei) 41 (5) 573-8, (1994), JP 62-273259-A (= Chemical Abstract 109:83463w), JP 62-286961-A (= Derwent No. 88-025703/04), JP 62-201859-A (= Derwent No. 87-288481/41), JP 62-184056-A (= Derwent No. 87-266739/38), US 5019482 and J. of Photochemistry and Photobiology A 107, 261-269 (1997).

The use of hydroxamic acid ester sulfonates as thermal initiators for the polymerization of olefines in a temperature range from 50-350°C is described in EP 35291. The activation with light of these compounds is, however, not disclosed. Further, α -oximinoacid ester sulfonates are mentioned as thermal acid generators for thermosetting coating compositions in EP 44115 and by W.J.-Mijis et al. in J. Coatings Technology 1983, 55, 45.







In radical photopolymerization technology there still exists a need for highly reactive, easy to prepare and easy to handle photoinitiator systems. In addition, such new photoinitiators must meet the high requirements of the industry regarding properties like, for example, thermal stability and storage stability.

Surprisingly, it has now been found that specific oxime derivatives of the formulae I, II, III, IV, V and/or VI, as described below, are especially suitable as photoinitiators for radical photopolymerization in combination with coinitiators.

In accordance with the invention, the compounds of the formulae I, II, III, IV, V and/or VI can be used as radical photoinitiators for the photopolymerization of ethylenically unsaturated compounds or of mixtures which comprise such compounds.

The invention therefore relates to a radically photopolymerizable composition comprising

- (a) at least one ethylenically unsaturated photopolymerizable compound,
- (b) as photoinitiator, at least one compound of the formula I, II, III, IV, V and/or VI



wherein

m is 0 or 1;

n is 0, 1, 2 or 3;

x is 1 or 2;

R₁ is phenyl, phenyl which is substituted by one or more of the radicals C₁-C₁₂alkyl, C₁-C₄-haloalkyl, halogen, phenyl, OR₁₀, NR₁₁R₁₂, SR₁₃ and/or -S-phenyl, it being possible for the

substituents OR_{10} , SR_{13} and $NR_{11}R_{12}$ to form 5- or 6-membered rings, via the radicals R_{10} , R_{11} , R_{12} and/or R_{13} , with further substituents on the phenyl ring or with one of the carbon atoms of the phenyl ring,

or R_1 is naphthyl, anthracyl or phenanthryl, the radicals naphthyl, anthracyl and phenanthryl being unsubstituted or substituted by C_1 - C_6 alkyl, phenyl, OR_{10} , $NR_{11}R_{12}$, SR_{13} and/or -S-phenyl, it being possible for the substituents OR_{10} , SR_{13} and $NR_{11}R_{12}$ to form 5- or 6-membered rings, via the radicals R_{10} , R_{11} , R_{12} and/or R_{13} with further substituents on the naphthyl, anthracyl or phenanthryl ring or with one of the carbon atoms of the naphthyl, anthracyl or phenanthryl ring,

or R_1 is a heteroaryl radical which is unsubstituted or substituted by C_1 - C_6 alkyl, phenyl, OR_{10} , $NR_{11}R_{12}$, SR_{13} and/or -S-phenyl, it being possible for the substituents OR_{10} , SR_{13} and $NR_{11}R_{12}$ to form 5- or 6-membered rings, via the radicals R_{10} , R_{11} , R_{12} and/or R_{13} with further substituents on the heteroaryl ring or with one of the carbon atoms of the heteroaryl ring; or R_1 is C_2 - C_{12} alkenyl, C_4 - C_8 cycloalkenyl, or C_6 - C_{12} bicycloalkenyl,

or, if m is zero, R_1 in the formula I additionally is benzoyl, 2-furoyl, 2-thiophenecarbonyl, 2-pyridinecarbonyl or 2-pyrrolecarbonyl, wherein the radicals benzoyl, 2-furoyl, 2-thiophenecarbonyl, 2-pyridinecarbonyl or 2-pyrrolecarbonyl are unsubstituted or substituted by one or more of the radicals C_1 - C_{12} alkyl, C_1 - C_4 haloalkyl, halogen, phenyl, OR_{10} , $NR_{11}R_{12}$, SR_{13} and/or -S-phenyl, it being possible for the substituents OR_{10} , SR_{13} and $NR_{11}R_{12}$ to form 5- or 6-membered rings, via the radicals R_{10} , R_{11} , R_{12} and/or R_{13} , with further substituents on the benzoyl, 2-furoyl, 2-thiophenecarbonyl, 2-pyridinecarbonyl or 2-pyrrolecarbonyl ring or with one of the carbon atoms of the benzoyl, 2-furoyl, 2-thiophenecarbonyl, 2-pyridinecarbonyl or 2-pyrrolecarbonyl ring;

or, if m is zero, n is 1 and simultaneously R_5 is phenyl which is unsubstituted or substituted by one or more C_1 - C_{12} alkyl, C_1 - C_4 haloalkyl, halogen, phenyl, OR_{10} , $NR_{11}R_{12}$, SR_{13} and/or -S-phenyl, R_1 in formula I additionally is hydrogen;

or, if m is 0 and n is 0, R_1 in formula I additionally is CN, hydrogen or C_1 - C_{12} alkyl, with the proviso that R_1 and R_2 are not simultaneously hydrogen or alkyl;

R'_1 is C_2 - C_{12} alkylene, phenylene, naphthylene, , diphenylene or

oxydiphenylene, these radicals are unsubstituted or substituted by C_1 - C_{12} alkyl;

R_2 has one of the meanings of R_1 or is phenyl, CN-substituted phenyl, C_2 - C_6 alkanoyl, benzoyl which is unsubstituted or substituted by C_1 - C_6 alkyl, phenyl, OR_{10} , SR_{13} , $NR_{11}R_{12}$ and/or -S-phenyl, or R_2 is CN, phenoxycarbonyl, NO_2 , C_1 - C_4 haloalkyl, C_2 - C_6 alkoxycarbonyl,


$S(O)_y-C_1-C_6$ alkyl, $S(O)_y-C_6-C_{12}$ aryl, C_1-C_{12} alkyl-substituted $S(O)_y-C_6-C_{12}$ aryl, $SO_2O-C_1-C_6$ alkyl, $SO_2O-C_6-C_{10}$ aryl, diphenylphosphinoyl or $NHCONH_2$,

or, if m is 1, R_1 and R_2 together with the CO group may form a 5- or 6-membered ring which is unsubstituted or substituted by C_1-C_6 alkyl, phenyl, OR_{10} , SR_{13} , $NR_{11}R_{12}$ and/or -S-phenyl, said ring may additionally be interrupted by -O-, -S-, -N(R_{11})- and/or by CO, and to said ring may be fused one or more benzo radicals;


y is 1 or 2;

R_3 if x is 1 is C_1-C_{18} alkylsulfonyl, phenyl- C_1-C_3 alkylsulfonyl, camphorylsulfonyl, C_1-C_{10} haloalkylsulfonyl, phenylsulfonyl, naphthylsulfonyl, anthracylsulfonyl or phenanthrylsulfonyl, wherein the groups phenyl, naphthyl, anthracyl and phenanthryl of the radicals phenyl- C_1-C_3 alkylsulfonyl, phenylsulfonyl, naphthylsulfonyl, anthracylsulfonyl and phenanthrylsulfonyl are unsubstituted or substituted by one or more halogen, C_1-C_4 haloalkyl, CN, NO_2 , C_1-C_{16} alkyl, phenyl, C_1-C_4 alkylthio, OR_{10} , $COOR_{13}$, C_1-C_4 alkyl-OCO-, $R_{13}OSO_2$ - and/or


- $NR_{11}R_{12}$; or R_3 is C_2-C_6 haloalkanoyl, halobenzoyl, or a group $\begin{array}{c} Y_1 \\ || \\ -P-R_{14} \\ | \\ R_{15} \end{array}$, $\begin{array}{c} Y_1 \\ || \\ -P-R_{14} \\ | \\ Y_2-R_{16} \end{array}$,



R_3 if x is 2, is C_2-C_{12} alkylenedisulfonyl, phenylenedisulfonyl, naphthylenedisulfonyl,



wherein the groups phenylene, naphthylene, $\text{---} \text{C}_6\text{H}_4 \text{---} CH_2 \text{---} \text{C}_6\text{H}_4 \text{---}$, diphenylene and oxydiphenylene of the radicals phenylenedisulfonyl, naphthylenedisulfonyl,



unsubstituted or substituted by C_1-C_{12} alkyl;

R_4 and R_5 are independently of each other hydrogen, halogen, C_1-C_8 alkyl, C_1-C_6 alkoxy,



C₁-C₄haloalkyl, CN, NO₂, C₂-C₆alkanoyl, benzoyl, phenyl, -S-phenyl, OR₁₀, SR₁₃, NR₁₁R₁₂, C₂-C₆alkoxycarbonyl, phenoxycarbonyl, S(O)_yC₁-C₆alkyl, S(O)_yC₆-C₁₂aryl, C₁-C₁₂alkyl-substituted S(O)_yC₆-C₁₂aryl, SO₂O-C₁-C₆alkyl, SO₂O-C₆-C₁₀aryl or NHCONH₂, or R₄ and R₅ together are a direct bond or -C(R₂₁)=C(R₂₂)-C(R₂₃)=C(R₂₄)-;

R₆, R₇, R₈ independently of one another are hydrogen, R₂₆Y-, phenyl optionally substituted by C₁-C₄alkyl or C₁-C₄alkyl-Y; or R₆, R₇ and R₈ are C₁-C₈ alkyl optionally substituted by halogen, OH, OR₂₅, COOR₂₅, or C₁-C₄-alkyl-COO-, or optionally interrupted by one or more -O-;


or R₆ and R₇ together with the atoms to which they are bound form a 5- or 6-membered saturated or unsaturated ring which is unsubstituted or substituted by one or more C₁-C₄alkyl and which ring optionally is interrupted by one or more Y or to which ring other rings are condensed;

R₉ is C₅-C₈cycloalkyl, phenyl, optionally substituted by C₁-C₄alkyl; or is C₁-C₁₂alkyl, optionally substituted by halogen, OH, or OR₂₅, or optionally interrupted by one or more -O-;


A is -S-, -O-, -NR₁₀-, or a group of formula A1, A2, A3 or A4



(A2),



(A3),



(A4);

Q is C₁-C₈-alkylene optionally interrupted by one or more -O-;

X is -O- or -NR₉-

Y, Y₁, Y₂ and Y₃ independently of one another are -O- or -S-;

Z is -CR₂₈- or -N-; and

Z₁ is -CH₂-, -S-, -O- or -NR₁₀-;

R₁₀ is hydrogen, phenyl, C₁-C₁₂alkyl which is unsubstituted or substituted by phenyl, OH, C₁-C₁₂alkoxy, C₁-C₁₂alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or by C₂-C₆-alkanoyl or R₁₀ is C₂-C₁₂alkyl interrupted by one or more -O-, said interrupted C₂-C₁₂alkyl is unsubstituted or substituted by phenyl, OH, C₁-C₁₂alkoxy, C₁-C₁₂alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or by C₂-C₆alkanoyl;

R₁₁ and R₁₂ independently of one another are hydrogen, C₁-C₁₂alkyl which is unsubstituted or substituted by OH, C₁-C₄alkoxy, C₁-C₁₂alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl

and/or C₁-C₆alkanoyl; or R₁₁ and R₁₂ are C₂-C₁₂alkyl interrupted by one or more -O-, said interrupted C₂-C₁₂alkyl is unsubstituted or substituted by OH, C₁-C₄alkoxy, C₁-C₁₂alkyl-sulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or C₁-C₆alkanoyl; or R₁₁ and R₁₂ are phenyl, C₂-C₆alkanoyl, benzoyl, C₁-C₆alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl, naphthylsulfonyl, anthracylsulfonyl or phenanthrylsulfonyl, or R₁₁ and R₁₂, together with the nitrogen atom to which they are bonded, form a 5-, 6- or 7-membered ring which may be interrupted by -O- or by -NR₁₀-;

R₁₃ is C₁-C₁₂alkyl which is unsubstituted or substituted by OH and/or C₁-C₄alkoxy or R₁₃ is C₂-C₁₂alkyl interrupted by one or more -O-, said interrupted C₂-C₁₂alkyl is unsubstituted or substituted by OH and/or C₁-C₄alkoxy;

R₁₄ and R₁₅ independently of one another are C₁-C₆alkyl which is unsubstituted or substituted by halogen or phenyl or R₁₄ and R₁₅ are phenyl which is unsubstituted or substituted by C₁-C₄alkyl or halogen;

R₁₆ and R₁₇ independently of one another have one of the meanings of R₁₄, or R₁₆ and R₁₇ together are 1,2-phenylene or C₂-C₆alkylene which is unsubstituted or substituted by C₁-C₄alkyl or halogen;

R₁₈, R₁₉ and R₂₀ independently of each other are C₁-C₆alkyl which is unsubstituted or substituted by halogen, or R₁₈, R₁₉ and R₂₀ are phenyl which is unsubstituted or substituted by C₁-C₄alkyl or halogen, or R₁₉ and R₂₀ together are 2,2'-biphenylene or C₂-C₆alkylene which is unsubstituted or substituted by C₁-C₄alkyl or halogen;

R₂₁, R₂₂, R₂₃ and R₂₄ independently of each other are hydrogen, C₁-C₄alkyl, halogen, phenyl, OR₁₀, SR₁₃, NR₁₁R₁₂, -S-phenyl, C₂-C₆alkoxycarbonyl, phenoxycarbonyl, CN, NO₂, C₁-C₄haloalkyl, S(O)_yC₁-C₆alkyl, S(O)_yC₆-C₁₂aryl, C₁-C₁₂alkyl-substituted S(O)_yC₆-C₁₂aryl, SO₂O-C₁-C₆alkyl, SO₂O-C₆-C₁₀aryl or NHCONH₂;

R₂₅ is C₁-C₈ alkyl optionally substituted by halogen, OH, or C₁-C₄-alkoxy or optionally interrupted by one or more -O-;

R₂₆ is phenyl, optionally substituted by C₁-C₄alkyl or C₁-C₄alkyl-Y; or is C₁-C₈ alkyl optionally substituted by halogen, OH, OR₂₅, COOR₂₅, or C₁-C₄alkyl-COO-, or optionally interrupted by one or more -O-;

R₂₇ and R₂₈ independently of one another have one of the meanings given for R₄, or R₂₇ and R₂₈ together are -CO-NR₁₀CO-, or -C(R₂₁)=C(R₂₂)-C(R₂₃)=C(R₂₄)-; and

(c) at least one coinitiator.

C₁-C₁₂alkyl is linear or branched and is, for example, C₁-C₈-, C₁-C₆- or C₁-C₄alkyl. Examples are methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, pentyl, hexyl, heptyl, 2,4,4-trimethylpentyl, 2-ethylhexyl, octyl, nonyl, decyl, undecyl or dodecyl, especially C₁-C₆alkyl, preferably C₁-C₄alkyl, such as methyl, isopropyl or butyl. Of interest are, for example, C₁-C₈-, especially C₁-C₆-, preferably C₁-C₄-alkyl, such as methyl or butyl.

C₂-C₁₂alkyl, which is interrupted once or several times by -O- or by -NR₆-, is interrupted, for example, from one to five times, for example from one to three times or once or twice, by -O- or -NR₆-. The interrupting O-atoms in the chain are non-successive. This results in structural units as for example: -O(CH₂)₂OCH₃, -O(CH₂CH₂O)₂CH₂CH₃, -CH₂-O-CH₃, -CH₂CH₂-O-CH₂CH₃, -[CH₂CH₂O]_y-CH₃, wherein y is an integer of 1-5, -(CH₂CH₂O)₅CH₂CH₃, -CH₂-CH(CH₃)-O-CH₂-CH₂CH₃ or -CH₂-CH(CH₃)-O-CH₂-CH₃.


If alkyl groups are interrupted one or more times by Y they are interrupted, for example, from one to five times, for example from one to three times or once or twice, by Y. If Y is -O-, the interrupting O-atoms in the chain are non-successive.

C₂-C₁₂alkenyl radicals may be mono or polyunsaturated, linear or branched and are for example C₂-C₈-, C₂-C₆- or C₂-C₄alkenyl. Examples are allyl, methallyl, vinyl, 1,1-dimethylallyl, 1-butenyl, 3-butenyl, 2-butenyl, 1,3-pentadienyl, 5-hexenyl or 7-octenyl, especially allyl or vinyl.

C₄-C₈cycloalkenyl, may have one or more double bonds and is for example C₄-C₆-cycloalkenyl or C₆-C₈-cycloalkenyl. Examples are cyclobutenyl, cyclopentenyl, cyclohexenyl or cyclooctenyl, especially cyclopentenyl and cyclohexenyl, preferably cyclohexenyl.

C₆-C₁₂bicycloalkenyl refers to a bicyclic alkenyl group, which may possess one or more double bonds and wherein the double bonds are either situated in the same ring, but may also be situated in both rings. If several double bonds are present in the bicyclus, the double bonds are conjugated or non-conjugated, preferably the double bonds are conjugated. At least one of the double bonds of the bicycloalkenyl radical is conjugated with the double bond of formula I, II which is substituted by the radicals R₄ and R₅. Examples are bicyclo[4.2.4]dodec-3,7-dien-5-yl, bicyclo[4.2.4]dodec-3-en-5-yl, bicyclo[4.2.4]dodec-4-en-6-yl, bicyclo[4.2.3]-non-3-en-5-yl, bicyclo[4.2.3]-non-4-en-6-yl, bicyclo[4.2.3]-non-7-en-8-yl, bicyclo-


[4.2.3]-non-8-en-7-yl, wherein the examples are referring to the following numbering



C_1 - C_{12} Alkylene and C_1 - C_8 alkylene are linear or branched and are, for example, C_1 - C_6 -, C_1 - C_4 -, C_2 - C_8 -, C_2 - C_6 - or C_2 - C_4 -alkylene. Examples are methylene, ethylene, propylene, butylene, pentylene, hexylene, heptylene, octylene, nonylene, decylene, undecylene and dodecylene, especially C_1 - C_6 alkylene, preferably C_1 - C_4 alkylene, such as methylene or butylene.

C_2 - C_{12} alkylenedisulfonyl accordingly is an alkylene radical as indicated above, which at both "yl"-moieties bears a sulfonyl group. Examples are $-\text{SO}_2-(\text{CH}_2\text{CH}_2)_z-\text{SO}_2-$, with $z = 1-6$, e.g. $-\text{SO}_2-\text{CH}_2\text{CH}_2-\text{SO}_2-$, or $-\text{SO}_2-\text{CH}(\text{CH}_3)\text{CH}_2-\text{SO}_2-$.


Phenylenedisulfonyl, diphenylenedisulfonyl and oxydiphenylenedisulfonyl also bear the sulfonyl groups at the "yl" moiety. Accordingly, resulting structures are




Substituted phenyl carries from one to five, for example one, two or three, especially one or two, substituents on the phenyl ring. The substitution is, for example in the 2-, 3-, 4-, 6-, 3,4-, 2,6-, 2,4-, 2,4,6- or 3,4,5-position of the phenyl ring.


When the radicals naphthyl, phenanthryl, heteroaryl and anthracyl are substituted by one or more radicals, they are, for example, mono- to penta-substituted, for example mono-, di- or tri-substituted, especially mono- or di-substituted.



When R_1 is a phenyl radical substituted by OR_{10} , $\text{NR}_{11}\text{R}_{12}$ and/or by SR_{13} and the substituents OR_{10} , $\text{NR}_{11}\text{R}_{12}$ and SR_{13} form 5- or 6-membered rings, via the radicals R_{10} , R_{11} , R_{12} or R_{13} , with other substituents on the phenyl ring or with one of the carbon atoms of the

phenyl ring, for example the following structural units are obtained 




In the present application, the term "heteroaryl" denotes unsubstituted and substituted radicals, for example 2-thienyl, , , wherein R_{11} and R_{12} are as


defined above, thianthrenyl, isobenzofuranyl, xanthenyl, phenoxanthiyl,  or


, wherein X is S, O or NR_9 and R_9 is as defined above. Examples thereof are pyrazolyl, thiazolyl, oxazolyl, isothiazolyl or isoxazolyl. Also included are, for example, furyl, pyrrolyl, 1,2,4-triazolyl,  or 5-membered ring heterocycles having a fused-on aromatic

group, for example benzimidazolyl, benzothienyl, benzofuranyl, benzoxazolyl and benzothiazolyl.


Other examples of "heteroaryls" are pyridyl, especially 3-pyridyl, , wherein R_{10}

is as defined above, pyrimidinyl, pyrazinyl, 1,3,5-triazinyl, 2,4-, 2,2- or 2,3-diazinyl, indolizinyl, isoindolyl, indolyl, indazolyl, purinyl, isoquinolyl, quinolyl, phenoxazinyl or phenazinyl. In this Application, the term "heteroaryl" also denotes the radicals thioxanthyl, xanthyl,



ed above,  or anthraquinonyl. Each of the heteroaryls may carry the substituents indicated above or in claim 1.

When R_1 and R_2 together with the CO group form a 5- or 6-membered ring, it is, for example, a cyclopentanone, or cyclohexanone ring. There may be fused to that ring, for example, also benzo, naphtho, anthraceno, phenanthreno or heteroaryl radicals, thereby forming



is as defined above, and in which structures the aromatic rings may carry further substituents as defined above and in claim 1.

Apparently these structures are not strictly " R_1 and R_2 together", but are partial illustrations of the final compounds.

They are, for example, also benzoquinone, naphthoquinone or anthraquinone radicals.

C_1 - C_6 Alkanoyl is, for example, formyl, acetyl, propionyl, butanoyl or hexanoyl, especially acetyl.

C_1 - C_{12} Alkoxy is a linear or branched radical and is C_1 - C_8 -, C_1 - C_6 -, C_1 - C_4 alkoxy, for example, methoxy, ethoxy, propoxy, isopropoxy, n-butyloxy, sec-butyloxy, isobutyloxy, tert-butyloxy, pentyloxy, hexyloxy, heptyloxy, 2,4,4-trimethylpentyloxy, 2-ethylhexyloxy, octyloxy, nonyloxy, decyloxy or dodecyloxy, especially methoxy, ethoxy, propoxy, isopropoxy, n-butyloxy, sec-butyloxy, iso-butyloxy or tert-butyloxy, preferably methoxy. C_1 - C_6 alkoxy is has the same meanings as given above up to the corresponding number of C-atoms.

C_2 - C_6 Alkoxy carbonyl is $(C_1$ - C_5 alkyl)-O-C(O)-, wherein C_1 - C_5 alkyl is as defined above up to the appropriate number of carbon atoms. Examples are methoxycarbonyl, ethoxycarbonyl,

propoxycarbonyl, butoxycarbonyl or pentyloxycarbonyl, wherein the alkyl radicals having more than two carbon atoms are linear or branched.

C₁-C₄haloalkyl is C₁-C₄alkyl mono- or poly-substituted by halogen, C₁-C₄alkyl is as defined above. There are, for example, from one to three or one or two halogen substituents at the alkyl radical. Examples are chloromethyl, trichloromethyl, trifluoromethyl or 2-bromopropyl, especially trifluoromethyl or trichloromethyl.


C₂-C₆haloalkanoyl is (C₁-C₅haloalkyl)-C(O)-, wherein C₁-C₅haloalkyl is linear or branched C₁-C₅alkyl mono- or poly-substituted by halogen. Examples are chloroacetyl, trichloroacetyl, trifluoroacetyl, pentafluoropropionyl, perfluorooctanoyl, or 2-bromopropionyl, especially trifluoroacetyl or trichloroacetyl.

Halobenzoyl is benzoyl which is mono- or poly-substituted by halogen and/or C₁-C₄haloalkyl, wherein C₁-C₄haloalkyl is as defined above. Examples are pentafluorobenzoyl, trichlorobenzoyl, trifluoromethylbenzoyl, especially pentafluorobenzoyl.


Halogen is fluorine, chlorine, bromine or iodine, especially chlorine or fluorine, preferably fluorine.

In a group S(O)_y-C₆-C₁₀aryl which is unsubstituted or substituted by C₁-C₁₂alkyl, the aryl radical is, for example, phenyl, tolyl, dodecylphenyl or 1- or 2-naphthyl.


Phenyl-C₁-C₃alkyl is, for example, benzyl, 2-phenylethyl, 3-phenylpropyl, α-methylbenzyl or α,α-dimethylbenzyl, especially benzyl.

Oxydiphenylene is . Dialkoxyphosphinoxyl is for example di(C₁-C₁₂alkoxy)-phosphinoyl, and corresponds also to the different meanings for "C₁-C₁₂alkoxy" given above. Preferred is diethoxyphosphinoyl.

When R_{11} and R_{12} together with the nitrogen atom to which they are bonded form a 5-, 6- or 7-membered ring that may be interrupted by -O- or by -NR₁₀-, for example the following structures are obtained




When R_4 and R_5 together are $-(CR_{21})=C(R_{22})-C(R_{23})=C(R_{24})-$ the following structures are formed



and A are as defined above or in claim 1.

When R_6 and R_7 together with the atoms to which they are bound form a 5- or 6-membered saturated or unsaturated ring which is unsubstituted or substituted by one or more C₁-C₄alkyl and which ring optionally is interrupted by one or more Y or to which ring other rings are

condensed the following structures can be formed:



One or more substituents C₁-C₄alkyl are for example 1 to 3, 1 or 2, in particular 1 substituent. Rings which optionally are condensed to the rings formed by R_6 and R_7 are for example phenyl rings.

The terms "and/or" or "or/and" in the present context are meant to express that not only one of the defined alternatives (substituents) may be present, but also several of the defined alternatives (substituents) together, namely mixtures of different alternatives (substituents).


The term "at least" is meant to define one or more than one, for example one or two or three, preferably one or two.

Preference is given to compositions wherein the compounds of formula I, II, III, IV, V and VI.

R_3 if x is 1 is C_1 - C_{18} alkylsulfonyl, phenyl- C_1 - C_3 alkylsulfonyl, camphorylsulfonyl, C_{10} haloalkylsulfonyl, phenylsulfonyl, naphthylsulfonyl, anthracylsulfonyl or phenanthrylsulfonyl, wherein the groups phenyl, naphthyl, anthracyl and phenanthryl of the radicals phenyl- C_1 - C_3 alkylsulfonyl, phenylsulfonyl, naphthylsulfonyl, anthracylsulfonyl and phenanthrylsulfonyl are unsubstituted or substituted by one or more halogen, C_1 - C_4 haloalkyl, CN, NO_2 , C_1 - C_{16} alkyl, phenyl, C_1 - C_4 alkylthio, OR_{10} , $COOR_{13}$, C_1 - C_4 alkyl- OCO -, $R_{13}OSO_2$ -


and/or $-NR_{11}R_{12}$; or R_3 is a group $\begin{array}{c} Y_1 \\ || \\ -P-R_{14} \\ | \\ R_{15} \end{array}$, $\begin{array}{c} Y_1 \\ || \\ -P-R_{14} \\ | \\ Y_2-R_{16} \end{array}$, $\begin{array}{c} Y_1 \\ || \\ -P-Y_3-R_{17} \\ | \\ Y_2-R_{16} \end{array}$;

R_3 if x is 2 is C_2 - C_{12} alkylenedisulfonyl, phenylenedisulfonyl, naphthylenedisulfonyl,



wherein the groups phenylene, naphthylene, $\begin{array}{c} \text{C}_6\text{H}_4 \\ | \\ \text{CH}_2 \\ | \\ \text{C}_6\text{H}_4 \end{array}$, diphenylene and

oxydiphenylene of the radicals phenylenedisulfonyl, naphthylenedisulfonyl,





unsubstituted or substituted by C_1 - C_{12} alkyl; and

Y_1 , Y_2 and Y_3 independently of each other are -O- or -S-.

Further compositions of interest are those wherein component (b) is a compound of formula I, II or III, wherein m is zero.


Interesting are compositions comprising as component (b) a compound of formula Ia or IIa



n is 0 or 1;

R_1 , R'_1 , R_2 , R_3 , R_4 , R_5 and x are as defined above.

Further preferred is a composition, wherein component (b) is a compound of formula IIIa



R_1 , R_2 , R_3 , R_4 , R_5 , A and x are as defined above.

wherein

Special mention should be made of compositions wherein wherein component (b) is a compound of formula I, III, V or VI wherein

n and m independently of one another are 0 or 1;


x is 1;

R_1 is phenyl which unsubstituted or substituted once or twice by C_1 - C_4 alkyl, halogen, OR_{10} or SR_{13} ;

R'_1 is phenylene;

R_2 is C_2 - C_6 alkoxycarbonyl, or CN;

R_3 is C_1 - C_8 alkylsulfonyl, or phenylsulfonyl, wherein the group phenyl of the radical phenylsulfonyl is unsubstituted or substituted by C_1 - C_8 alkyl or OR_{10} ; or R_3 is a group,



R_4 and R_5 independently of one another are hydrogen or C_1 - C_8 alkyl;

R_6 is hydrogen;

R_{12} is hydrogen or C_1 - C_4 alkyl;

R_{10} and R_{13} independently of one another are C_1 - C_4 alkyl;

A is -S-;

Y_1 , Y_2 and Y_3 are -O-;


X is -O- or $-NR_9$;

Q is C_1 - C_8 -alkylene optionally interrupted by -O-;

R_{14} and R_{15} independently of one another are phenyl or C_1 - C_4 alkyl-substituted phenyl;


R_{16} and R_{17} independently of one another are C_1 - C_4 alkyl.

The invention relates also the novel oxime derivatives of formula V or VI



wherein

R_3 is C_1 - C_{18} alkylsulfonyl, phenyl- C_1 - C_3 alkylsulfonyl, camphorylsulfonyl, C_1 - C_{18} haloalkylsulfonyl, phenylsulfonyl, naphthylsulfonyl, anthracylsulfonyl or phenanthrylsulfonyl, wherein the groups phenyl, naphthyl, anthracyl and phenanthryl of the radicals phenyl- C_1 - C_3 alkylsulfonyl, phenylsulfonyl, naphthylsulfonyl, anthracylsulfonyl and phenanthrylsulfonyl are unsubstituted or substituted by one or more halogen, C_1 - C_4 haloalkyl, CN, NO_2 , C_1 - C_{16} alkyl, phenyl, C_1 - C_4 alkylthio, OR_{10} , $COOR_{13}$, C_1 - C_4 alkyl-OCO-, $R_{13}OSO_2$ - and/or $-NR_{11}R_{12}$; or R_3 is C_2 - C_6 haloalkanoyl, halobenzoyl, or a group



R_6 , R_7 , R_8 independently of each other are hydrogen, $R_{26}Y$ -, phenyl optionally substituted by C_1 - C_4 alkyl or C_1 - C_4 alkyl- Y -; or R_6 , R_7 and R_8 are C_1 - C_8 alkyl optionally substituted by halogen, OH, OR_{25} , $COOR_{25}$, or C_1 - C_4 -alkyl-COO-, or optionally interrupted by one or more -O-;

or R_6 and R_7 together with the atoms to which they are bound form a 5- or 6-membered saturated or unsaturated ring which is unsubstituted or substituted by one or more C_1 - C_4 alkyl and which ring optionally is interrupted by one or more Y or to which ring other rings are condensed;

Q is C_1 - C_8 -alkylene optionally interrupted by one or more -O-;

X is -O- or $-NR_9$ -;

Y, Y_1 , Y_2 and Y_3 independently of each other are -O- or -S-;

R_9 is C_5 - C_8 cycloalkyl, phenyl, optionally substituted by C_1 - C_4 alkyl; or is C_1 - C_{12} alkyl, optionally substituted by halogen, OH, or OR_{25} , or optionally interrupted by one or more -O-;

R₂₅ is C₁-C₈alkyl optionally substituted by halogen, OH, or C₁-C₄-alkoxy or optionally interrupted by one or more -O-;

R₂₆ is phenyl, optionally substituted by C₁-C₄alkyl or C₁-C₄alkyl-Y; or is C₁-C₈ alkyl optionally substituted by halogen, OH, OR₂₅, COOR₂₅, or C₁-C₄alkyl-COO-, or optionally interrupted by one or more -O-;

with the proviso that if R₃ is CH₃C₆H₄SO₂-, R₆, R₇ and R₈ are hydrogen and X is oxygen, then R₉ is not methyl or ethyl;

R₁₀ is hydrogen, phenyl, C₁-C₁₂alkyl which is unsubstituted or substituted by phenyl, OH, C₁-C₁₂alkoxy, C₁-C₁₂alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or by C₂-C₆-alkanoyl or R₁₀ is C₂-C₁₂alkyl interrupted by one or more -O-, said interrupted C₂-C₁₂alkyl is unsubstituted or substituted by phenyl, OH, C₁-C₁₂alkoxy, C₁-C₁₂alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or by C₂-C₆alkanoyl;

R₁₁ and R₁₂ independently of one another are hydrogen, C₁-C₁₂alkyl which is unsubstituted or substituted by OH, C₁-C₄alkoxy, C₁-C₁₂alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or C₁-C₆alkanoyl; or R₁₁ and R₁₂ are C₂-C₁₂alkyl interrupted by one or more -O-, said interrupted C₂-C₁₂alkyl is unsubstituted or substituted by OH, C₁-C₄alkoxy, C₁-C₁₂alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or C₁-C₆alkanoyl; or R₁₁ and R₁₂ are phenyl, C₂-C₆alkanoyl, benzoyl, C₁-C₆alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl, naphthylsulfonyl, anthracylsulfonyl or phenanthrylsulfonyl, or R₁₁ and R₁₂, together with the nitrogen atom to which they are bonded, form a 5-, 6- or 7-membered ring which may be interrupted by -O- or by -NR₁₀-;

R₁₃ is C₁-C₁₂alkyl which is unsubstituted or substituted by OH and/or C₁-C₄alkoxy or is C₂-C₁₂alkyl interrupted by one or more -O-, said interrupted C₂-C₁₂alkyl is unsubstituted or substituted by OH and/or C₁-C₄alkoxy;

R₁₄ and R₁₅ independently of one another are C₁-C₆alkyl which is unsubstituted or substituted by halogen, or are phenyl which is unsubstituted or substituted by C₁-C₄alkyl or halogen;


R₁₆ and R₁₇ independently of one another have one of the meanings of R₁₄; or R₁₆ and R₁₇ together are 1,2-phenylene or C₂-C₆alkylene which is unsubstituted or substituted by C₁-C₄alkyl or halogen;

R₁₈, R₁₉ and R₂₀ independently of each other are C₁-C₆alkyl, which is unsubstituted or substituted by halogen; or are phenyl which is unsubstituted or substituted by C₁-C₄alkyl or halogen, or R₁₉ and R₂₀ together are 2,2'-biphenylene or C₂-C₆alkylene which is unsubstituted or substituted by C₁-C₄alkyl or halogen.

Preference is given especially to compounds of formula V and VI wherein

R_3 is unsubstituted or fluorine-substituted C_1 - C_4 -alkylsulfonyl, unsubstituted or fluorine-

substituted phenylsulfonyl, C_1 - C_{12} -alkylphenylsulfonyl or a group $\begin{array}{c} Y_1 \\ || \\ -P-R_{14} \\ | \\ R_{15} \end{array}$,



R_6 , R_7 and R_8 independently of each other are hydrogen, $R_{26}Y$ -, phenyl optionally substituted by C_1 - C_4 alkyl or C_1 - C_4 alkyl- Y -; or R_6 , R_7 and R_8 are C_1 - C_8 alkyl optionally substituted by OH, OR_{25} , or $COOR_{25}$, or optionally interrupted by one or more -O-; or R_6 and R_7 together with the atoms to which they are bound form a 5- or 6-membered saturated or unsaturated ring which is unsubstituted or substituted by one or more C_1 - C_4 alkyl and which ring optionally is interrupted by one or more Y or to which ring other rings are condensed;

Q is C_1 - C_8 -alkylene optionally interrupted by one or more -O-;

Y is -O- or -S-;

Y_1 , Y_2 and Y_3 are -O-;

X is -O- or - NR_9 -;

R_9 is cyclohexyl, phenyl, optionally substituted by C_1 - C_4 alkyl; or is C_1 - C_{12} alkyl, optionally substituted by OH, or OR_{25} , or optionally interrupted by one or more -O-;


R_{25} is C_1 - C_8 alkyl optionally substituted by OH or C_1 - C_4 -alkoxy or optionally interrupted by one or more -O-;

R_{26} is phenyl, optionally substituted by C_1 - C_4 alkyl or C_1 - C_4 alkyl- Y ; or is C_1 - C_8 alkyl optionally substituted by OH, OR_{25} , or $COOR_{25}$; or optionally interrupted by one or more -O-;

with the proviso that if R_3 is $CH_3C_6H_4SO_2$ -, R_6 , R_7 and R_8 are hydrogen and X is oxygen, then R_9 is not methyl or ethyl.

Especially preferred are compounds of formula V or VI, wherein

R_3 is C_1 - C_4 -alkylsulfonyl, phenylsulfonyl, C_1 - C_{12} -alkylphenylsulfonyl or a group



R_6 , R_7 , R_8 independently of each other are hydrogen, C_1 - C_4 alkyl, or $R_{26}Y$ -,

or R_6 and R_7 together with the atoms to which they are bound form a 5- or 6-membered saturated or unsaturated ring which is unsubstituted or substituted by one or more C_1 - C_4 alkyl and which ring optionally is interrupted by one or more Y or to which ring other rings are condensed;

Q is C_1 - C_8 -alkylene optionally interrupted by one or more -O-;

X is -O- or -NR₉-;

R_9 is C_1 - C_6 alkyl, optionally interrupted by one or more -O-;

R_{26} is C_1 - C_4 alkyl;

Y_1 and Y_2 are O;

R_{14} and R_{15} independently of one another are phenyl or methylphenyl;

R_{16} and R_{17} independently of one another are C_1 - C_4 -alkyl;

with the proviso that if R_3 is $CH_3C_6H_4SO_2$ -, R_6 , R_7 and R_8 are hydrogen and X is O, then R_9 is not methyl or ethyl.

Interesting are further compounds of formula V and VI, wherein

R_3 is C_1 - C_4 -alkylsulfonyl, phenylsulfonyl, or C_1 - C_{12} -alkylphenylsulfonyl;

R_6 , R_7 , R_8 independently of one another are hydrogen, C_1 - C_4 alkyl, $R_{26}Y$ - or phenyl, or R_6 and R_7 together with the atoms to which they are bound form a 5- or 6-membered saturated or unsaturated ring which optionally is substituted by one or more C_1 - C_4 alkyl and which ring is optionally interrupted by Y or to which ring other rings are condensed;

Q is C_1 - C_8 -alkylene optionally interrupted by one or more -O-;

X is -O-;

R_9 is C_1 - C_6 alkyl-, optionally interrupted by one or more -O-;

R_{26} is C_1 - C_4 alkyl;

with the proviso that, if R_3 is $CH_3C_6H_4SO_2$ -, R_6 , R_7 and R_8 are hydrogen and X is oxygen, then R_9 is not methyl or ethyl.

Other interesting compounds of formulae V and VI are such, wherein


R_3 is C_1 - C_4 -alkylsulfonyl, phenylsulfonyl, or C_1 - C_{12} -alkylphenylsulfonyl;

R_6 , R_7 , R_8 independently of one another are hydrogen, C_1 - C_4 alkyl, or $R_{26}Y$ -;

X is $-NR_9$ -; and

R_9 is C_1 - C_6 alkyl-, optionally interrupted by one or more $-O-$.

Further interesting are compounds of formulae V and VI, wherein



R_6 , R_7 , R_8 independently of one another are hydrogen, $R_{26}Y$ -, C_1 - C_8 alkyl optionally substituted by OH, OR_{25} , or $COOR_{25}$, or optionally interrupted by one or more $-O-$, or R_6 and R_7 together with the atoms to which they are bound form a 5- or 6-membered saturated or unsaturated ring which is unsubstituted or substituted by one or more C_1 - C_4 alkyl, or to which ring other rings are condensed;

Y is $-O-$ or $-S-$;


X is $-O-$ or $-NR_9$ -;

R_9 is phenyl, C_1 - C_{12} alkyl, optionally substituted by OH, or OR_{25} , or optionally interrupted by one or more $-O-$;

R_{25} is C_1 - C_8 alkyl which is unsubstituted or substituted by OH, O - C_1 - C_4 -alkyl or interrupted by one or more $-O-$;

R_{26} is phenyl, C_1 - C_8 alkyl optionally substituted by OH, OR_{25} , or $COOR_{25}$, or optionally interrupted by one or more $-O-$.

Other interesting compounds of formulae V and VI are compounds, wherein



R_6 , R_7 , R_8 independently of one another are hydrogen, C_1 - C_4 alkyl, or $R_{26}Y$ -;

X , Y_1 and Y_2 are $-O-$;

x is 1;

R_9 is C_1 - C_6 alkyl, optionally interrupted by one or more $-O-$;


R_{26} is C_1 - C_4 alkyl ;


R₁₄ and R₁₅ independently of each other are phenyl or methylphenyl; and
R₁₆ and R₁₇ independently of each other are C₁-C₄-alkyl.

Most preferred are the compounds methyl α -(methylsulfonyloxyimino)-2-phenylacetate, propyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate, methylethyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate, butyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate, hexyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate, 2-methoxyethyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylphenyl)acetate, propyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylphenyl)acetate, butyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylphenyl)acetate, 2-methoxyethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylphenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-ethylphenyl)acetate, ethyl α -(4-butylphenylsulfonyloxyimino)-2-(4-methylphenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-fluorophenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methoxyphenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(3,4-dimethoxyphenyl)acetate, 2-methoxyethyl α -(4-methylphenylsulfonyloxyimino)-2-(3,4-dimethoxyphenyl)acetate, 2-methoxyethyl α -(methylsulfonyloxyimino)-2-(3,4-dimethoxyphenyl)acetate, methyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylthiophenyl)acetate, methyl α -(methylsulfonyloxyimino)-2-(4-methylthiophenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylthiophenyl)acetate, 2-methoxyethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylthiophenyl)acetate, 2-methoxyethyl α -(methylsulfonyloxyimino)-2-(4-methylthiophenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(3,4-butylthiophenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-dimethylaminophenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(thianthren-2-yl)acetate, methylsulfonyloxyimino-3,4-dimethoxyphenyl acetic acid 2-[2-(methylsulfonyloxyimino-3,4-dimethoxyphenyl-acetoxy)-ethoxy]-ethyl ester; N,N-diethyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetamide, N,N-diethyl α -(methylsulfonyloxyimino)-2-phenylacetamide, N,N-dibutyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetamide, N,N-diethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-ethylphenyl)acetamide, methyl α -(diethoxyphosphoryloxyimino)-2-phenylacetate, ethyl α -(diethoxyphosphoryloxyimino)-2-phenylacetate, propyl α -(diethoxyphosphoryloxyimino)-2-phenylacetate; 2-methoxyethyl α -(diethoxyphosphoryloxyimino)-2-(3,4-dimethoxyphenyl)acetate, methyl α -(diethoxyphosphoryloxyimino)-2-(4-methylthiophenyl)acetate, ethyl α -(diethoxyphosphoryloxyimino)-2-(4-methylthiophenyl)acetate.

The invention also relates to mixtures of isomeric forms of the compounds of formula I, II, III, IV, V and VI. The double bond of the oxime group can exist in both the syn (cis, *Z*) and the anti (trans, *E*) form or as mixtures of the two geometrical isomers. In addition, the *n* double bonds of formulae I and II can, depending on the substituents R_4 and R_5 , exhibit two (*Z* and *E*) configurations. The substituted methyldene group $C(R_1)R_2$ of formula III and IV can also exhibit two (cis and trans) isomers. Depending on R_4 , R_5 and *A*, this can result in up to four geometrical isomers. In the present invention, both the individual geometrical isomers and any mixtures of two or more geometrical isomers can be used.

Oxime derivatives (of formulae of formula I, II, III, IV, V and VI) can be prepared by methods described in the literature, for example by reacting suitable free oximes ($R_3 = H$) with the desired (for example, sulfonic) acid halides (for example, R_3Cl or $Cl-R_3-Cl$).





$R_1, R_2, R_3, R_4, R_5, R_6, R_7, R_8, R_9, X, x, n$ and m are defined as described above.

These reactions are carried out in an inert solvent such as toluene, tetrahydrofuran (THF) or dimethylformamide (DMF) in the presence of a base, for example a tertiary amine, such as triethylamine, or by reaction of the salt of an oxime with the desired acid chloride. These methods are disclosed, for example, in EP 48615. The sodium salts of oximes can be obtained, for example, by reacting the oxime in question with a sodium alcoholate in dimethylformamide.

The compounds of formulae II, IV and VI are prepared in an analogous manner by starting with the corresponding dimeric hydroxyimino compounds.

The starting oximes ($R_3 = H$) can be prepared in numerous ways, which are known to the person skilled in the art, for example by the nitrosation of "active" methylene groups with nitrous acid or an alkyl nitrite. Both alkaline conditions, as described for example in *Organic Syntheses* coll. Vol. VI (J. Wiley & Sons, New York, 1988), pp 199 and 840, and acidic conditions, as described, for example, in *Organic Synthesis* coll. Vol V, pp 32 and 373, coll. Vol. III, pp 191 and 513, coll. Vol.II, pp. 202, 204 and 363, are suitable for the preparation of the oximes used as starting materials in the invention. Nitrous acid is usually generated from sodium nitrite. The alkyl nitrite can be for example methyl nitrite, ethyl nitrite, isopropyl nitrite, butyl nitrite, isoamyl nitrite. Another example is the oximation of cinnamaldehydes (*Synthesis* 1994, 573) followed by cyanation (*J. Org. Chem.* 1993, 58, 2075).


The oximes of formula X required for the reaction can be prepared according to known procedures, for example by reacting benzyl cyanides or cyanomethyl heterocycles with nitrobenzenes or nitronapthalenes in the presence of a base (such as, for example, sodium methoxide or potassium hydroxide) in a polar solvent such as, for example, methanol or DMF, as described by R.B. Davis, L.C. Pizzini & E.J. Bara, J. Org. Chem. 26, 4270 (1961) or P. Fournary and T. Marey, Bull. Soc. Chim. Fr. 3223 (1968). Temperatures of -80°C to 80°C , especially -10°C to 60°C are suitable for the reaction. Phase transfer catalysis is also suitable to prepare oxime intermediates of formula X. K.Takahashi, et al. have described the use of benzyltriethyl ammonium chloride and 50% aqueous sodium hydroxide for the reaction of nitrobenzene with benzyl cyanide (K.Takahashi, T.Tsuboi, K. Yamada, H. Iida, Nippon Kagaku Kaishi 144-7 (1976); Chemical Abstract No. 84:105162).

Oximes of formula X have also been prepared as intermediates in the synthesis of various pharmaceutical compounds (e.g. US 5043327, US 5521187, EP 371564, EP541153, ES 524551) or for use as UV absorbers (for instance, in US 3374248).

Oximes can also be obtained by reacting a suitable carbonyl or thionylcarbonyl compounds with hydroxylamine or a hydroxylammonium salt.

The preparation of the chlorides used to introduce the radical R_3 is known to the person skilled in the art. Many of these compounds are commercially available.

Another process for the preparation of the compounds according to the invention consists in that a ketone or an α -keto ester is brought into reaction with a solution of hydroxylamine or preferably a solution of the hydroxylamine hydrochloride salt thereof. Thus, α -(hydroxyimino)-2-phenylacetic acid ester can be conveniently prepared by the reaction of the corresponding α -keto phenylacetic acid ester with hydroxylamine or hydroxylamine hydrochloride in the presence of a base such as a tertiary amine or pyridine:



$\text{R}_6, \text{R}_7, \text{R}_8$ and R_9 have the meaning indicated above.

If requested, a solvent, such as for example diethyl ether, tert-butyl-methy-ether, dichloromethane or tetrahydrofuran, can be used. When the corresponding amides are used as starting materials, α -(hydroxyimino)-2-phenylacetic acid amides are obtained by the same procedure.

The composition according to the invention may additionally to the components (a), (b) and (c) comprise a binder polymer (d), and/or at least one further photoinitiator (e), and/or other additives (f) customary in the art.

The unsaturated compounds (a) may include one or more olefinic double bonds. They may be of low (monomeric) or high (oligomeric) molecular mass. Examples of monomers containing a double bond are alkyl or hydroxyalkyl acrylates or methacrylates, for example methyl, ethyl, butyl, 2-ethylhexyl or 2-hydroxyethyl acrylate, isobornyl acrylate, methyl methacrylate or ethyl methacrylate. Silicone acrylates are also advantageous. Other examples are acrylonitrile, acrylamide, methacrylamide, N-substituted (meth)acrylamides, vinyl esters such as vinyl acetate, vinyl ethers such as isobutyl vinyl ether, styrene, alkyl- and halostyrenes, N-vinylpyrrolidone, vinyl chloride or vinylidene chloride.

Examples of monomers containing two or more double bonds are the diacrylates of ethylene glycol, propylene glycol, neopentyl glycol, hexamethylene glycol or of bisphenol A, and 4,4'-bis(2-acryloyloxyethoxy)diphenylpropane, trimethylolpropane triacrylate, pentaerythritol triacrylate or tetraacrylate, vinyl acrylate, divinylbenzene, divinyl succinate, diallyl phthalate, triallyl phosphate, triallyl isocyanurate or tris(2-acryloylethyl) isocyanurate.

Examples of polyunsaturated compounds of relatively high molecular mass (oligomers) are acrylized epoxy resins, acrylized polyesters, polyesters containing vinyl ether or epoxy groups, and also polyurethanes and polyethers. Further examples of unsaturated oligomers are unsaturated polyester resins, which are usually prepared from maleic acid, phthalic acid and one or more diols and have molecular weights of from about 500 to 3000. In addition it is also possible to employ vinyl ether monomers and oligomers, and also maleate-terminated oligomers with polyester, polyurethane, polyether, polyvinyl ether and epoxy main chains. Of particular suitability are combinations of oligomers which carry vinyl ether groups and of polymers as described in WO 90/01512. However, copolymers of vinyl ether and maleic acid-

functionalized monomers are also suitable. Unsaturated oligomers of this kind can also be referred to as prepolymers.

Particularly suitable examples are esters of ethylenically unsaturated carboxylic acids and polyols or polyepoxides, and polymers having ethylenically unsaturated groups in the chain or in side groups, for example unsaturated polyesters, polyamides and polyurethanes and copolymers thereof, polybutadiene and butadiene copolymers, polyisoprene and isoprene copolymers, polymers and copolymers containing (meth)acrylic groups in side chains, and also mixtures of one or more such polymers.

Examples of unsaturated carboxylic acids are acrylic acid, methacrylic acid, crotonic acid, itaconic acid, cinnamic acid, and unsaturated fatty acids such as linolenic acid or oleic acid. Acrylic and methacrylic acids are preferred.

Suitable polyols are aromatic and, in particular, aliphatic and cycloaliphatic polyols. Examples of aromatic polyols are hydroquinone, 4,4'-dihydroxydiphenyl, 2,2-di(4-hydroxyphenyl)propane, and also novolaks and resols. Examples of polyepoxides are those based on the abovementioned polyols, especially the aromatic polyols, and epichlorohydrin. Other suitable polyols are polymers and copolymers containing hydroxyl groups in the polymer chain or in side groups, examples being polyvinyl alcohol and copolymers thereof or polyhydroxyalkyl methacrylates or copolymers thereof. Further polyols which are suitable are oligoesters having hydroxyl end groups.

Examples of aliphatic and cycloaliphatic polyols are alkylenediols having preferably 2 to 12 C atoms, such as ethylene glycol, 1,2- or 1,3-propanediol, 1,2-, 1,3- or 1,4-butanediol, pentanediol, hexanediol, octanediol, dodecanediol, diethylene glycol, triethylene glycol, polyethylene glycols having molecular weights of preferably from 200 to 1500, 1,3-cyclopentanediol, 1,2-, 1,3- or 1,4-cyclohexanediol, 1,4-dihydroxymethylcyclohexane, glycerol, tris(β -hydroxyethyl)amine, trimethylolethane, trimethylolpropane, pentaerythritol, dipentaerythritol and sorbitol.

The polyols may be partially or completely esterified with one carboxylic acid or with different unsaturated carboxylic acids, and in partial esters the free hydroxyl groups may be modified, for example etherified or esterified with other carboxylic acids.

Examples of esters are:

trimethylolpropane triacrylate, trimethylolethane triacrylate, trimethylolpropane trimethacrylate, trimethylolethane trimethacrylate, tetramethylene glycol dimethacrylate, triethylene glycol dimethacrylate, tetraethylene glycol diacrylate, pentaerythritol diacrylate, pentaerythritol triacrylate, pentaerythritol tetraacrylate, dipentaerythritol diacrylate, dipentaerythritol triacrylate, dipentaerythritol tetraacrylate, dipentaerythritol pentaacrylate, dipentaerythritol hexaacrylate, tripentaerythritol octaacrylate, pentaerythritol dimethacrylate, pentaerythritol trimethacrylate, dipentaerythritol dimethacrylate, dipentaerythritol tetramethacrylate, tripentaerythritol octamethacrylate, pentaerythritol diitaconate, dipentaerythritol trisitaconate, dipentaerythritol pentaitaconate, dipentaerythritol hexaitaconate, ethylene glycol diacrylate, 1,3-butanediol diacrylate, 1,3-butanediol dimethacrylate, 1,4-butanediol diitaconate, sorbitol triacrylate, sorbitol tetraacrylate, pentaerythritol-modified triacrylate, sorbitol tetramethacrylate, sorbitol pentaacrylate, sorbitol hexaacrylate, oligoester acrylates and methacrylates, glycerol diacrylate and triacrylate, 1,4-cyclohexane diacrylate, bisacrylates and bismethacrylates of polyethylene glycol with a molecular weight of from 200 to 1500, or mixtures thereof.

Also suitable as components (a) are the amides of identical or different, unsaturated carboxylic acids with aromatic, cycloaliphatic and aliphatic polyamines having preferably 2 to 6, especially 2 to 4, amino groups. Examples of such polyamines are ethylenediamine, 1,2- or 1,3-propylenediamine, 1,2-, 1,3- or 1,4-butylenediamine, 1,5-pentylenediamine, 1,6-hexylenediamine, octylenediamine, dodecylenediamine, 1,4-diaminocyclohexane, isophoronediamine, phenylenediamine, bisphenylenediamine, di- β -aminoethyl ether, diethylenetriamine, triethylenetetramine, di(β -aminoethoxy)- or di(β -aminopropoxy)ethane. Other suitable polyamines are polymers and copolymers, preferably with additional amino groups in the side chain, and oligoamides having amino end groups. Examples of such unsaturated amides are methylenebisacrylamide, 1,6-hexamethylenebisacrylamide, diethylenetriaminetris-methacrylamide, bis(methacrylamidopropoxy)ethane, β -methacrylamidoethyl methacrylate and $\text{N}[(\beta\text{-hydroxyethoxy})\text{ethyl}]\text{acrylamide}$.

Suitable unsaturated polyesters and polyamides are derived, for example, from maleic acid and from diols or diamines. Some of the maleic acid can be replaced by other dicarboxylic acids. They can be used together with ethylenically unsaturated comonomers, for example styrene. The polyesters and polyamides may also be derived from dicarboxylic acids and

from ethylenically unsaturated diols or diamines, especially from those with relatively long chains of, for example 6 to 20 C atoms. Examples of polyurethanes are those composed of saturated or unsaturated diisocyanates and of unsaturated or, respectively, saturated diols.

Polybutadiene and polyisoprene and copolymers thereof are known. Examples of suitable comonomers are olefins, such as ethylene, propene, butene and hexene, (meth)acrylates, acrylonitrile, styrene or vinyl chloride. Polymers with (meth)acrylate groups in the side chain are likewise known. They may, for example, be reaction products of epoxy resins based on novolaks with (meth)acrylic acid, or may be homo- or copolymers of vinyl alcohol or hydroxyalkyl derivatives thereof which are esterified with (meth)acrylic acid, or may be homo- and copolymers of (meth)acrylates which are esterified with hydroxyalkyl (meth)acrylates.

The photopolymerizable compounds can be used alone or in any desired mixtures. It is preferred to use mixtures of polyol (meth)acrylates.

Examples of the component (a) are also polymers or oligomers having at least two ethylenically unsaturated groups and at least one carboxyl function within the molecule structure, such as acid modified epoxyacrylates (for example, EB9696, UCB Chemicals; KAYARAD TCR1025, Nippon Kayaku Co., LTD.), or acrylated acrylicopolymers (for example, ACA200M, Daicel Industries, Ltd.).

As component (a), a mono- or multi-functional ethylenically unsaturated compound, or mixtures of said compounds, can be included in the above composition up to 98 % by weight based on the solid portion of the composition.

The unsaturated compounds (a) can also be used as a mixture with non-photopolymerizable, film-forming components. These may, for example, be physically drying polymers or solutions thereof in organic solvents, for instance nitrocellulose or cellulose acetobutyrate. They may also, however, be chemically and/or thermally curable (heat-curable) resins, examples being polyisocyanates, polyepoxides and melamine resins, as well as polyimide precursors. The use of heat-curable resins at the same time is important for use in systems known as hybrid systems, which in a first stage are photopolymerized and in a second stage are crosslinked by means of thermal postcure.

In the compositions according to the invention acrylate systems are especially preferred.

As examples of the coinitiator component (c), these are, in particular, aromatic compounds, for example benzophenone and derivatives thereof, thioxanthone and derivatives thereof, anthraquinone and derivatives thereof, coumarin and phenothiazine and derivatives thereof, and also 3-(aroylmethylene)thiazolines, rhodanine, camphorquinone, but also eosine, rhodamine, erythrosine, xanthene, thioxanthene, acridine, e.g. 9-phenylacridine, 1,7-bis(9-acridinyl)heptane, 1,5-bis(9-acridinyl)pentane, cyanine and merocyanine dyes.

Specific examples coinitiators suitable as component (c) in the compositions according to the invention are

1. Thioxanthenes

Thioxanthone, 2-isopropylthioxanthone, 2-chlorothioxanthone, 2-dodecylthioxanthone, 2,4-diethylthioxanthone, 2,4-dimethylthioxanthone, 1-methoxycarbonylthioxanthone, 2-ethoxycarbonylthioxanthone, 3-(2-methoxyethoxycarbonyl)-thioxanthone, 4-butoxycarbonylthioxanthone, 3-butoxycarbonyl-7-methylthioxanthone, 1-cyano-3-chlorothioxanthone, 1-ethoxycarbonyl-3-chlorothioxanthone, 1-ethoxycarbonyl-3-ethoxythioxanthone, 1-ethoxycarbonyl-3-aminothioxanthone, 1-ethoxycarbonyl-3-phenylsulfurylthioxanthone, 3,4-di-[2-(2-methoxyethoxy)-ethoxycarbonyl]-thioxanthone, 1-ethoxycarbonyl-3-(1-methyl-1-morpholinoethyl)-thioxanthone, 2-methyl-6-dimethoxymethyl-thioxanthone, 2-methyl-6-(1,1-dimethoxybenzyl)-thioxanthone, 2-morpholinomethylthioxanthone, 2-methyl-6-morpholinomethylthioxanthone, N-allylthioxanthone-3,4-dicarboximide, N-octylthioxanthone-3,4-dicarboximide, N-(1,1,3,3-tetramethylbutyl)-thioxanthone-3,4-dicarboximide, 1-phenoxythioxanthone, 6-ethoxycarbonyl-2-methoxythioxanthone, 6-ethoxycarbonyl-2-methylthioxanthone, thioxanthone-2-carboxylic acid polyethyleneglycol ester, 2-hydroxy-3-(3,4-dimethyl-9-oxo-9H-thioxanthen-2-yl)oxy)-N,N,N-trimethyl-1-propanaminium chloride;

2. Benzophenones

benzophenone, 4-phenyl benzophenone, 4-methoxy benzophenone, 4,4'-dimethoxy benzophenone, 4,4'-dimethyl benzophenone, 4,4'-dichlorobenzophenone, 4,4'-bis(dimethylamino)-benzophenone, 4,4'-bis(diethylamino)benzophenone, 4-methyl benzophenone, 2,4,6-trimethylbenzophenone, 4-(4-methylthiophenyl)-benzophenone, 3,3'-dimethyl-4-methoxy benzophenone, methyl-2-benzoylbenzoate, 4-(2-hydroxyethylthio)-benzophenone, 4-(4-tolylthio)-benzophenone, 4-benzoyl-N,N,N-trimethylbenzenemethanaminium chloride, 2-hydroxy-3-(4-benzoylphenoxy)-N,N,N-trimethyl-1-propanaminium chloride monohydrate, 4-(13-acryloyl-

1,4,7,10,13-pentaoxatridecyl)-benzophenone, 4-benzoyl-N,N-dimethyl-N-[2-(1-oxo-2-propenyl)oxy]ethyl-benzenemethanaminium chloride;

3. Coumarins

Coumarin 1, Coumarin 2, Coumarin 6, Coumarin 7, Coumarin 30, Coumarin 102, Coumarin 106, Coumarin 138, Coumarin 152, Coumarin 153, Coumarin 307, Coumarin 314, Coumarin 314T, Coumarin 334, Coumarin 337, Coumarin 500, 3-benzoyl coumarin, 3'-benzoyl-7-methoxycoumarin, 3-benzoyl-5,7-dimethoxycoumarin, 3-benzoyl-5,7-dipropoxycoumarin, 3-benzoyl-6,8-dichlorocoumarin, 3-benzoyl-6-chloro-coumarin, 3,3'-carbonyl-bis[5,7-di(propoxy)-coumarin], 3,3'-carbonyl-bis(7-methoxycoumarin), 3,3'-carbonyl-bis(7-diethylamino-coumarin), 3-isobutyroylcoumarin, 3-benzoyl-5,7-dimethoxy-coumarin, 3-benzoyl-5,7-diethoxy-coumarin, 3-benzoyl-5,7-dibutoxycoumarin, 3-benzoyl-5,7-di(methoxyethoxy)-coumarin, 3-benzoyl-5,7-di(allyloxy)coumarin, 3-benzoyl-7-dimethylaminocoumarin, 3-benzoyl-7-diethylaminocoumarin, 3-isobutyroyl-7-dimethylaminocoumarin, 5,7-dimethoxy-3-(1-naphthoyl)-coumarin, 5,7-diethoxy-3-(1-naphthoyl)-coumarin, 3-benzoylbenzo[f]coumarin, 7-diethylamino-3-thienoylcoumarin, 3-(4-cyanobenzoyl)-5,7-dimethoxycoumarin, 3-(4-cyanobenzoyl)-5,7-dipropoxycoumarin, 7-dimethylamino-3-phenylcoumarin, 7-diethylamino-3-phenylcoumarin, the coumarin derivatives disclosed in JP 09-179299A and JP 09-325209A, for example 7-[(4-chloro-6-(diethylamino)-S-triazine-2-yl)amino]-3-phenylcoumarin;

4. 3-(aroylmethylene)-thiazolines

3-methyl-2-benzoylmethylene- β -naphthothiazoline, 3-methyl-2-benzoylmethylene-benzothiazoline, 3-ethyl-2-propionylmethylene- β -naphthothiazoline;

5. Rhodanines

4-dimethylaminobenzalrhodanine, 4-diethylaminobenzalrhodanine, 3-ethyl-5-(3-octyl-2-benzothiazolinyldene)-rhodanine, the rhodanine derivatives, formulae [1], [2], [7], disclosed in JP 08-305019A;

6. Other compounds

acetophenone, 3-methoxyacetophenone, 4-phenylacetophenone, benzil, 4,4'-bis(dimethylamino)benzil, 2-acetylnaphthalene, 2-naphthaldehyde, dansyl acid derivatives, 9,10-anthraquinone, anthracene, pyrene, aminopyrene, perylene, phenanthrene, phenanthrenequinone, 9-fluorenone, dibenzosuberone, curcumin, xanthone, thiomichler's ketone, α -(4-dimethylaminobenzylidene) ketones, e.g. 2,5-bis(4-diethylaminobenzylidene)cyclopentanone, 2-(4-dimethylamino-benzylidene)-indan-1-one, 3-(4-dimethylamino-phenyl)-1-indan-5-yl-propenone, 3-phenylthiophthalimide, N-methyl-3,5-di(ethylthio)-phthalimide, N-methyl-3,5-di(ethylthio)-phthalimide, phenothiazine, methylphenothiazine, amines, e.g. N-phenylglycine, ethyl 4-di-

methylaminobenzoate, butoxyethyl 4-dimethylaminobenzoate, 4-dimethylaminoacetophenone, triethanolamine, methyldiethanolamine, dimethylaminoethanol, 2-(dimethylamino)ethyl benzoate.

A photopolymerizable composition, comprising as coinitiator (c) a compound selected from the group consisting of benzophenone derivatives, thioxanthone derivatives or coumarin derivatives is preferred.

The photopolymerizable compositions generally contain 0.005 to 20 % by weight, for example 0.05 to 20 % by weight, preferably 0.01 to 10 % by weight, in particular 0.1 to 10 % by weight, of the coinitiator, based on the solid composition.

Interesting is a photopolymerizable composition, comprising additionally at least one binder polymer (d).

As component (d), binders as well can be added to the novel compositions. This is particularly expedient when the photopolymerizable compounds are liquid or viscous substances. The quantity of binder may, for example, be 2-98 %, preferably 5-95 % and especially 20-90 %, by weight relative to the overall solids content. The choice of binder is made depending on the field of application and on properties required for this field, such as the capacity for development in aqueous and organic solvent systems, adhesion to substrates and sensitivity to oxygen.

Examples of suitable binders are polymers having a molecular weight of about 2000 to 2000000, preferably 5000 to 1000000. Examples of alkali developable binders are acrylic polymer having carboxylic acid function as a pendant group, such as conventionally known copolymers obtained by copolymerizing an ethylenic unsaturated carboxylic acid such as (meth)acrylic acid, 2-carboxyethyl (meth)acrylic acid, 2-carboxypropyl (meth)acrylic acid, itaconic acid, crotonic acid, maleic acid and fumaric acid, with one or more monomers selected from esters of (meth)acrylic acid, such as methyl (meth)acrylate, ethyl (meth)acrylate, propyl (meth)acrylate, butyl (meth)acrylate, benzyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, hydroxyethyl (meth)acrylate, hydroxypropyl (meth)acrylate, benzyl (meth)acrylate; vinyl aromatic compounds, such as styrene, α -methylstyrene, hydroxystyrene, vinyltoluene, p-chlorostyrene; amide type unsaturated compounds, (meth)acrylamide diacetoneacrylamide,

N-methylolacrylamide, N-butoxymethacrylamide; and polyolefin type compounds, such as butadiene, isoprene, chloroprene and the like; methacrylonitrile, methyl isopropenyl ketone, vinyl acetate, vinyl propionate, or vinyl pivalate.

Preferable examples of copolymers are copolymers of methyl methacrylate/methacrylic acid, copolymers of benzyl methacrylate/methacrylic acid, copolymers of methyl methacrylate/ethyl acrylate/methacrylic acid, copolymers of benzyl methacrylate/methacrylic acid/styrene, copolymers of benzyl methacrylate/methacrylic acid/hydroxyethyl methacrylate, copolymers of methyl methacrylate/butyl methacrylate/methacrylic acid/styrene, copolymers of methyl methacrylate/benzyl methacrylate/methacrylic acid/hydroxyphenyl methacrylate. Examples of solvent developable binder polymers are poly(alkyl methacrylates), poly(alkyl acrylates); cellulose esters and cellulose ethers, such as cellulose acetate, cellulose acetobutyrate, methylcellulose, ethylcellulose; polyvinylbutyral, polyvinylformal, cyclized rubber, polyethers such as polyethylene oxide, polypropylene oxide and polytetrahydrofuran; polystyrene, polycarbonate, polyurethane, chlorinated polyolefins, polyvinyl chloride, vinyl chloride/vinylidene copolymers, copolymers of vinylidene chloride with acrylonitrile, methyl methacrylate and vinyl acetate, polyvinyl acetate, copoly(ethylene/vinyl acetate), polymers such as polycaprolactam and poly(hexamethylenadipamide), and polyesters such as poly(ethylene glycol terephthalate) and poly(hexamethylene glycol succinate) and polyimides.

Preferred is a photopolymerizable composition, comprising as binder polymer (d), a copolymer of methacrylate and methacrylic acid.

In addition to the photoinitiator (b) and coinitiator (c) the photopolymerizable mixtures may include various additives (f), which are customary in the art and the choice of which depends on the intended end use of the composition. Examples of these are thermal inhibitors, which are intended to prevent premature polymerization, examples being hydroquinone, hydroquinone derivatives, p-methoxyphenol, β -naphthol or sterically hindered phenols, such as 2,6-di-tert-butyl-p-cresol. In order to increase the stability on storage in the dark it is possible, for example, to use copper compounds, such as copper naphthenate, stearate or octoate, phosphorus compounds, for example triphenylphosphine, tributylphosphine, triethyl phosphite, triphenyl phosphite or tribenzyl phosphite, quaternary ammonium compounds, for example tetramethylammonium chloride or trimethylbenzylammonium chloride, or hydroxylamine derivatives, for example N-diethylhydroxylamine. To exclude atmospheric oxygen during the polymerization it is possible to add paraffin or similar wax-like substances which,

being of inadequate solubility in the polymer, migrate to the surface in the beginning of polymerization and form a transparent surface layer which prevents the ingress of air. It is also possible to apply an oxygen-impermeable layer. Light stabilizers which can be added in a small quantity are UV absorbers, for example those of the hydroxyphenylbenzotriazole, hydroxyphenyl-benzophenone, oxalamide or hydroxyphenyl-s-triazine type. These compounds can be used individually or in mixtures, with or without sterically hindered amines (HALS).

Examples of such UV absorbers and light stabilizers are

1. 2-(2'-hydroxyphenyl)benzotriazoles for example 2-(2'-hydroxy-5'-methylphenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-5'-(1,1,3,3-tetramethylbutyl)phenyl)benzotriazole, 2-(3',5'-di-tert-butyl-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-methylphenyl)-5-chlorobenzotriazole, 2-(3'-sec-butyl-5'-tert-butyl-2'-hydroxyphenyl)benzotriazole, 2-(2'-hydroxy-4'-octoxyphenyl)benzotriazole, 2-(3',5'-di-tert-amyl-2'-hydroxyphenyl)benzotriazole, 2-(3',5'-bis-(α,α -dimethylbenzyl)-2'-hydroxyphenyl)-benzotriazole, mixture of 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonyl)ethyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethyl-hexyl-oxy)carbonyl]ethyl)-2'-hydroxyphenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonyl)ethyl)phenyl)-5-chlorobenzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-methoxycarbonyl)ethyl)phenyl)-benzotriazole, 2-(3'-tert-butyl-2'-hydroxy-5'-(2-octyloxycarbonyl)ethyl)phenyl)benzotriazole, 2-(3'-tert-butyl-5'-[2-(2-ethylhexyloxy)carbonyl]ethyl)-2'-hydroxyphenyl)benzotriazole, 2-(3'-dodecyl-2'-hydroxy-5'-methylphenyl)-benzotriazole, and 2-(3'-tert-butyl-2'-hydroxy-5'-(2-isooctyloxycarbonyl)ethyl)phenyl)benzotriazole, 2,2'-methylenebis[4-(1,1,3,3-tetramethylbutyl)-6-benzotriazol-2-yl-phenol]; transesterification product of 2-[3'-tert-butyl-5'-(2-methoxycarbonyl)ethyl]-2'-hydroxyphenyl)-benzotriazole with polyethylene glycol 300; $[R-CH_2CH_2-COO(CH_2)_3]_2$ where R = 3'-tert-butyl-4'-hydroxy-5'-2H-benzotriazol-2-yl-phenyl.

2. 2-Hydroxybenzophenones, for example the 4-hydroxy-, 4-methoxy-, 4-octoxy-, 4-decyloxy-, 4-dodecyloxy-, 4-benzyloxy-, 4,2',4'-trihydroxy- and 2'-hydroxy-4,4'-dimethoxy derivative.

3. Esters of substituted or unsubstituted benzoic acids, for example 4-tert-butylphenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoylresorcinol, bis(4-tert-butylbenzoyl)resorcinol, benzoylresorcinol, 2,4-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate, hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, octadecyl 3,5-di-tert-butyl-4-hydroxybenzoate, and 2-methyl-4,6-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate.

4. Acrylates, for example isooctyl or ethyl α -cyano- β , β -diphenyl acrylate, methyl α -carboxymethoxycinnamate, butyl or methyl α -cyano- β -methyl-p-methoxycinnamate, methyl α -carboxymethoxy-p-methoxycinnamate and N-(β -carbomethoxy- β -cyanovinyl)-2-methylindoline.

5. Sterically hindered amines, for example bis-(2,2,6,6-tetramethylpiperidyl) sebacate, bis-(2,2,6,6-tetramethylpiperidyl) succinate, bis-(1,2,2,6,6-pentamethylpiperidyl) sebacate, bis-(1,2,2,6,6-pentamethylpiperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, condensation product of 1-hydroxyethyl-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, condensation product of N,N'-bis-(2,2,6,6-tetramethyl-4-piperidyl)hexa-methylenediamine and 4-tert-octylamino-2,6-dichloro-1,3,5-s-triazine, tris-(2,2,6,6-tetramethyl-4-piperidyl) nitrioltriacetate, tetrakis-(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4-butane tetraoate, 1,1'-(1,2-ethandiyl)bis(3,3,5,5-tetramethyl-piperazinone), 4-benzoyl-2,2,6,6-tetramethylpiperidine, 4-stearyloxy-2,2,6,6-tetramethylpiperidine, bis-(1,2,2,6,6-pentamethylpiperidyl) 2-n-butyl-2-(2-hydroxy-3,5-di-tert-butylbenzyl) malonate, 3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, bis-(1-octyloxy-2,2,6,6-tetramethylpiperidyl) sebacate, bis-(1-octyloxy-2,2,6,6-tetramethylpiperidyl) succinate, condensation product of N,N'-bis-(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-morpholino-2,6-dichloro-1,3,5-triazine, condensation product of 2-chloro-4,6-di-(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)-1,3,5-triazine and 1,2-bis-(3-aminopropyl-amino)ethane, condensation product of 2-chloro-4,6-di-(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis-(3-aminopropylamino)-ethane, 8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, 3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidine-2,5-dione and 3-dodecyl-1-(1,2,2,6,6-penta-methyl-4-piperidyl)-pyrrolidine-2,5-dione.

6. Oxalamides, for example 4,4'-dioctyloxyoxanilide, 2,2'-diethoxyoxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butyloxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butyloxanilide, 2-ethoxy-2'-ethyl-oxanilide, N,N'-bis-(3-dimethylaminopropyl)oxalamide, 2-ethoxy-5-tert-butyl-2'-ethyloxanilide and its mixture with 2-ethoxy-2'-ethyl-5,4'-di-tert-butyloxanilide, mixtures of o- and p-methoxy- and of o- and p-ethoxy-disubstituted oxanilides.

7. 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxy-phenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-butyloxy-propyloxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[2-hydroxy-4-(2-hydroxy-3-octyloxy-propyloxy)phenyl]-4,6-

bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-[4-dodecyl/tridecyl-oxy-(2-hydroxypropyl)oxy-2-hydroxy-phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine.

8. Phosphites and phosphonites, for example triphenyl phosphite, diphenyl alkyl phosphites, phenyl dialkyl phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythrityl diphosphite, tris-(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythrityl diphosphite, bis-(2,4-di-tert-butylphenyl) pentaerythrityl diphosphite, bis-(2,6-di-tert-butyl-4-methylphenyl) pentaerythrityl diphosphite, bis-isodecyloxy pentaerythrityl diphosphite, bis-(2,4-di-tert-butyl-6-methylphenyl) pentaerythrityl diphosphite, bis-(2,4,6-tri-tert-butylphenyl) pentaerythrityl diphosphite, tristearyl sorbitol triphosphite, tetrakis-(2,4-di-tert-butylphenyl)-4,4'-biphenylene diphosphonite, 6-isooctyloxy-2,4,8,10-tetra-tert-butyl-12H-dibenzo[d,g]-1,3,2-dioxaphosphocine, 6-fluoro-2,4,8,10-tetra-tert-butyl-12-methyl-dibenzo[d,g]-1,3,2-dioxaphosphocine, bis-(2,4-di-tert-butyl-6-methylphenyl) methyl phosphite and bis(2,4-di-tert-butyl-6-methylphenyl) ethyl phosphite.

Further additives known in the art may be added as component (f), as for example flow improvers and adhesion promoters.

To accelerate the photopolymerization it is possible to add amines, for example triethanolamine, N-methyldiethanolamine. The action of the amines can be intensified by the addition of aromatic ketones. Examples of amines which can be used as oxygen scavengers are substituted N,N-dialkylanilines, as are described, for example, in EP 339841. Other accelerators and autoxidizers are thiols, thioethers, disulfides, phosphonium salts, phosphine oxides or phosphines, as described, for example, in EP 438123, GB 2180358 and JP Kokai Hei 6-68309.

It is further possible to add chain transfer agents which are customary in the art to the compositions according to the invention. Examples are mercaptans, amines and benzothiazol.

The curing process, in particular of compositions which are pigmented (for example with titanium dioxide), can be assisted by adding a component which under thermal conditions forms free radicals, for example an azo compound such as 2,2'-azobis(4-methoxy-2,4-dimethylvaleronitrile), a triazene, a diazo sulfide, a pentazadiene or a peroxy compound, for instance a hydroperoxide or peroxy carbonate, for example t-butyl hydroperoxide, as is described for example in EP 245639.

Further customary additives (f), depending on the intended use, are optical brighteners, fillers, pigments, dyes, wetting agents or levelling assistants.

In order to cure thick and pigmented coatings it can be appropriate to add glass microspheres or pulverized glass fibres, as described for example in US 5013768.

The choice of additive(s) (f) is made depending on the field of application and on properties required for this field. The additives described above are customary in the art and accordingly are added in amounts which are usual in the respective application.

In particular, further additives (f) are pigments which are added to the compositions according to the invention especially when these are used for the preparation of color filters. Examples of suitable pigments are given below.

In particular red, green, blue and black pigments are used as component (f).

The invention also provides compositions comprising as component (a) at least one ethylenically unsaturated photopolymerizable compound which is emulsified or dissolved in water. Many variants of such radiation-curable aqueous prepolymer dispersions are commercially available. A prepolymer dispersion is understood as being a dispersion of water and at least one prepolymer dispersed therein. The concentration of water in these systems is, for example, from 5 to 80 % by weight, in particular from 30 to 60 % by weight. The concentration of the radiation-curable prepolymer or prepolymer mixture is, for example, from 95 to 20 % by weight, in particular from 70 to 40 % by weight. In these compositions the sum of the percentages given for water and prepolymer is in each case 100, with auxiliaries and additives being added in varying quantities depending on the intended use.

The radiation-curable, film-forming prepolymers which are dispersed in water and are often also dissolved are aqueous prepolymer dispersions of mono- or polyfunctional, ethylenically unsaturated prepolymers which are known per se, can be initiated by free radicals and have for example a content of from 0.01 to 1.0 mol of polymerizable double bonds per 100 g of prepolymer and an average molecular weight of, for example, at least 400, in particular from 500 to 10000. Prepolymers with higher molecular weights, however, may also be considered depending on the intended application. Use is made, for example, of polyesters containing polymerizable C-C double bonds and having an acid number of not more than 10, of po-

lyethers containing polymerizable C-C double bonds, of hydroxyl-containing reaction products of a polyepoxide, containing at least two epoxide groups per molecule, with at least one α,β -ethylenically unsaturated carboxylic acid, of polyurethane (meth)acrylates and of acrylic copolymers which contain α,β -ethylenically unsaturated acrylic radicals, as are described in EP 12339. Mixtures of these prepolymers can likewise be used. Also suitable are the polymerizable prepolymers described in EP 33896, which are thioether adducts of polymerizable prepolymers having an average molecular weight of at least 600, a carboxyl group content of from 0.2 to 15 % and a content of from 0.01 to 0.8 mol of polymerizable C-C double bonds per 100 g of prepolymer. Other suitable aqueous dispersions, based on specific alkyl (meth)acrylate polymers, are described for example in EP 41125, and suitable water-dispersible, radiation-curable prepolymers of urethane acrylates can be found in DE 2936039. Some suitable UV curable urethane acrylate dispersions are supplied for example by ZENECA, such as NeoRad NR-440 and NeoRad NR-3709.

Further additives which may be included in the radiation-curable aqueous prepolymer dispersions are dispersion auxiliaries, emulsifiers, antioxidants, light stabilizers, dyes, pigments, fillers, for example talc, gypsum, silicic acid, rutile, carbon black, zinc oxide, iron oxides, reaction accelerators, levelling agents, lubricants, wetting agents, thickeners, flattening agents, antifoams and other auxiliaries customary in paint technology. Suitable dispersion auxiliaries are water-soluble organic compounds which are of high molecular mass and contain polar groups, examples being polyvinyl alcohols, polyvinylpyrrolidone or cellulose ethers. Emulsifiers which can be used are nonionic emulsifiers and, if desired, ionic emulsifiers as well. Such additives are added in customary amounts, known to the person skilled in the art, and depending of the intended use of the composition.

In certain cases it may be of advantage to use mixtures of two or more of the said photoinitiators (b). It is of course also possible to use mixtures with other known radical photoinitiators (e), for example mixtures with α -hydroxycyclohexyl phenyl ketone, 2-hydroxy-2-methyl-1-phenyl-propanone, α -hydroxy- or α -aminoacetophenones, e.g. (4-methylthiobenzoyl)-1-methyl-1-morpholinoethane, (4-morpholinobenzoyl)-1-benzyl-1-dimethylaminopropane, 4-aryloxy-1,3-dioxolanes, benzoin alkyl ethers, dimethyl benzil ketal, phenylglyoxalic esters and derivatives thereof, dimeric phenylglyoxalic esters, peresters, e.g. benzophenone tetracarboxylic peresters as described for example in EP 126541, monoacyl phosphine oxides, e.g. (2,4,6-trimethylbenzoyl)diphenylphosphine oxide, bisacylphosphine oxides, e.g. bis(2,6-dimethoxy-benzoyl)-(2,4,4-trimethyl-pentyl)phosphine oxide, bis(2,4,6-trimethylbenzoyl)-phen-

ylphosphine oxide, bis(2,4,6-trimethylbenzoyl)-2,4-dipentoxyphenylphosphine oxide, trisacylphosphine oxides, trihalomethyltriazines, e.g. 2-[2-(4-methoxyphenyl)vinyl]-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-(4-methoxyphenyl)-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-(3,4-dimethoxyphenyl)-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-methyl-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-[p-N,N-di(ethoxycarbonylmethyl)aminophenyl]-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-(4-methoxynaphthyl)-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-(1,3-benzodioxol-5-yl)-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-[2-(4-pentyloxyphenyl)vinyl]-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-[2-(3-methylfuran-2-yl)vinyl]-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-[2-(5-methylfuran-2-yl)vinyl]-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-[2-(2,4-dimethoxyphenyl)vinyl]-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-[2-(2-methoxyphenyl)vinyl]-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-[2-(4-isopropoxyphenyl)vinyl]-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-[2-(3-chloro-4-methoxy-phenyl)vinyl]-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-[2-bromo-4-N,N-di(ethoxycarbonylmethyl)aminophenyl]-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-[2-chloro-4-N,N-di(ethoxycarbonylmethyl)aminophenyl]-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-[3-bromo-4-N,N-di(ethoxycarbonylmethyl)aminophenyl]-4,6-bis(trichloromethyl)-1,3,5-triazine, 2-[3-chloro-4-N,N-di(ethoxycarbonylmethyl)aminophenyl]-4,6-bis(trichloromethyl)-1,3,5-triazine; or other halomethyl-triazines as described a) by G. Buhr, R. Dammel and C. Lindley in Polym. Mater. Sci. Eng. 61, 269 (1989), b) in EP 262788, furthermore halomethyl-oxazol photoinitiators, such as described in US 4371606 and US 4371607, 1,2-disulfones, such as described by E. A. Bartmann in Synthesis 5, 490 (1993); hexaarylbisimidazole/coinitiator systems, e.g. ortho-chlorohexaphenyl-bisimidazole combined with 2-mercaptobenzthiazole, borates, borate/coinitiator systems, O-acyloximes, e.g. benzophenoneoxime O-acetate, 4,4'-bis-(diethylamino)benzophenoneoxime O-acetate, 1-phenyl-1,2-propanedione-2-O-benzoyl oxime, oxime carbonates, e.g. 1-phenyl-1,2-propanedione-2-ethoxycarbonyl oxime, ferrocenium compounds, or titanocenes, e.g. bis(cyclopentadienyl)-bis(2,6-difluoro-3-pyrryl-phenyl)titanium.

Mention should be made of a photopolymerizable composition, comprising in addition to the photoinitiator (b) at least one further photoinitiator (e), and/or other additives (f), in particular pigments or dyes.

The photopolymerizable compositions generally contain 0.05 to 20 % by weight, preferably 0.1 to 10 % by weight, of the photoinitiator, based on the solid composition. The amount

refers to the sum of all photoinitiators added, if mixtures of initiators are employed. Accordingly, the amount either refers to the photoinitiator (b) or the photoinitiators (b) + (e).

The photopolymerizable compositions can be used for various purposes, for example as printing ink, as a clear finish, as a white finish, for example for wood or metal, as powder coating, as a coating material, inter alia for paper, wood, metal or plastic, as a daylight-curable coating for the marking of buildings and road marking, for photographic reproduction techniques, for holographic recording materials, for image recording techniques or to produce printing plates which can be developed with organic solvents or with aqueous alkalis, for producing masks for screen printing, as dental filling compositions, as adhesives, as pressure-sensitive adhesives, as laminating resins, as etch resists, electroplating resists, or permanent resists, both liquid and dry films, as photopatternable dielectric layer or coating and as solder masks for electronic circuits, as photosensitive materials to produce spacers, protective films, prism sheets or sealing materials in liquid crystalline displays, as resists to manufacture color filters (color mosaic) for any type of display applications or to generate structures in the manufacturing process of plasma-display panels and electroluminescence displays, for the production of optical switches, optical lattices (interference lattice), light circuits, for producing three-dimensional articles by mass curing (UV curing in transparent moulds) or by the stereolithography technique, as is described, for example, in US 4575330, to produce composite materials (for example styrenic polyesters, which may, if desired, contain glass fibres and/or other fibres and other auxiliaries) and other thick-layered compositions, for coating or sealing electronic components and chips, or as coatings for optical fibres, or for producing optical lenses, e.g. contact lenses or Fresnel lenses.

The compositions according to the invention are further suitable for the production of medical equipment, auxiliaries or implants.

Further the compositions according to the invention are suitable for the preparation of gels with thermotropic properties, as for example described in DE 19700064 and EP 678534.

The photoinitiators may additionally be employed as initiators for emulsion polymerizations, pearl polymerizations or suspension polymerizations, as polymerization initiators for fixing ordered states of liquid-crystalline monomers and oligomers, or as initiators for fixing dyes on organic materials.

In coating materials, use is frequently made of mixtures of a prepolymer with polyunsaturated monomers, which may additionally include a monounsaturated monomer as well. It is the prepolymer here which primarily dictates the properties of the coating film, and by varying it the skilled worker is able to influence the properties of the cured film. The polyunsaturated monomer functions as a crosslinking agent which renders the film insoluble. The monounsaturated monomer functions as a reactive diluent, which is used to reduce the viscosity without the need to employ a solvent.

Unsaturated polyester resins are usually used in two-component systems together with a monounsaturated monomer, preferably with styrene. For photoresists, specific one-component systems are often used, for example polymaleimides, polychalcones or polyimides, as described in DE 2308830.

The photoinitiators and mixtures thereof can also be used for the polymerization of radiation-curable powder coatings. The powder coatings can be based on solid resins and monomers containing reactive double bonds, for example maleates, vinyl ethers, acrylates, acrylamides and mixtures thereof. A free-radically UV-curable powder coating can be formulated by mixing unsaturated polyester resins with solid acrylamides (for example methyl methacrylamidoglycolate) and a novel free-radical photoinitiator, such formulations being as described, for example, in the paper "Radiation Curing of Powder Coating", Conference Proceedings, Radtech Europe 1993 by M. Wittig and Th. Gohmann. The powder coatings can also contain binders, as are described, for example, in DE 4228514 and in EP 636669. Free-radically UV-curable powder coatings can also be formulated by mixing unsaturated polyester resins with solid acrylates, methacrylates or vinyl ethers and with a novel photoinitiator (or photoinitiator mixture). The powder coatings may also comprise binders as are described, for example, in DE 4228514 and in EP 636669. The UV-curable powder coatings may additionally comprise white or coloured pigments. For example, preferably rutile titanium dioxide can be employed in concentrations of up to 50% by weight in order to give a cured powder coating of good hiding power. The procedure normally comprises electrostatic or tribostatic spraying of the powder onto the substrate, for example metal or wood, melting of the powder by heating, and, after a smooth film has formed, radiation-curing of the coating with ultraviolet and/or visible light, using for example medium-pressure mercury lamps, metal halide lamps or xenon lamps. A particular advantage of the radiation-curable powder coatings over their heat-curable counterparts is that the flow time after melting the powder particles can be delayed in order to ensure the formation of a smooth, high-gloss coating. In contrast to heat-

curable systems, radiation-curable powder coatings can be formulated to melt at lower temperatures without the unwanted effect of shortening their lifetime. For this reason, they are also suitable as coatings for heat-sensitive substrates, for example wood or plastics.

In addition to the photoinitiator systems, the powder coating formulations may also include UV absorbers. Appropriate examples are listed above.

The novel photocurable compositions are suitable, for example, as coating materials for substrates of all kinds, for example wood, textiles, paper, ceramics, glass, plastics such as polyesters, polyethylene terephthalate, polyolefins or cellulose acetate, especially in the form of films, and also metals such as Al, Cu, Ni, Fe, Zn, Mg or Co and GaAs, Si or SiO₂ to which it is intended to apply a protective layer or, by means of imagewise exposure, to generate an image.

Coating of the substrates can be carried out by applying to the substrate a liquid composition, a solution or a suspension. The choice of solvents and the concentration depend principally on the type of composition and on the coating technique. The solvent should be inert, i.e. it should not undergo a chemical reaction with the components and should be able to be removed again, after coating, in the course of drying. Examples of suitable solvents are ketones, ethers and esters, such as methyl ethyl ketone, isobutyl methyl ketone, 2-pentanone, 2-hexanone, cyclopentanone, cyclohexanone, N-methylpyrrolidone, dioxane, tetrahydrofuran, 2-methoxyethanol, 2-ethoxyethanol, 1-methoxy-2-propanol, 1,2-dimethoxyethane, ethyl acetate, ethoxyethyl acetate, n-butyl acetate, propylene glycol monomethyl ether acetate, diethylene glycol monoethyl ether acetate, ethyl lactate, methyl 3-methoxypropionate, methyl 3-ethoxypropionate, dipropylene glycol monomethyl ether and ethyl 3-ethoxypropionate. In certain cases it may be of advantage to use mixtures of two or more of the said solvents.

The solution is applied uniformly to a substrate by means of known coating techniques, for example by spin coating, dip coating, knife coating, curtain coating, brushing, spraying, especially by electrostatic spraying, and reverse-roll coating, and also by means of electrophoretic deposition. It is also possible to apply the photosensitive layer to a temporary, flexible support and then to coat the final substrate, for example a copper-clad circuit board, by transferring the layer via lamination.

The quantity applied (coat thickness) and the nature of the substrate (layer support) are dependent on the desired field of application. The range of coat thicknesses generally com-

prises values from about 0.05 μm to more than 100 μm , for example 0.05 μm to 1 cm, preferably 0.1 μm to 500 μm .

The photocurable compositions according to the invention are especially suitable for the preparation of thin films.

The novel radiation-sensitive compositions further find application as negative resists, having a very high sensitivity to light and being able to be developed in an aqueous alkaline medium without swelling. They are suitable as photoresists for electronics like electroplating resist, etch resist, both liquid and dry films, solder resist, as resists to manufacture color filters for any type of display applications or to generate structures in the manufacturing process of plasma-display panels and electroluminescence displays, the production of printing plates, such as offset printing plates or screen printing plates, for the production of printing forms for relief printing, planographic printing, rotogravure or of screen printing forms, for the production of relief copies, for example for the production of texts in braille, for the production of stamps, for use in chemical milling or as a microresist in the production of integrated circuits. The compositions further may be used as photopatternable dielectric layer or coating, encapsulating material and isolating coating in the production of computer chips, printed boards and other electric or electronic components. The possible layer supports, and the processing conditions of the coating substrates, are just as varied.

Because the photocurable compositions according to the invention have a good thermal stability and are sufficiently resistant to inhibition by oxygen, they are particularly suitable for the production of color filter or color mosaic systems, such as described, for example, in EP 320 264. Color filter systems usually are employed in the manufacturing of LCD displays or image sensors. The color filter systems usually are prepared by forming red, green and blue pixels and a black matrix on a glass substrate. In these processes photocurable compositions according to the invention can be employed. A particularly preferred method of use comprises the coating of the substrate with the composition of the invention, drying of the coating with a short heat treatment, patternwise exposure of the coating to actinic radiation and subsequent development of the pattern in an aqueous alkaline developer solution and finally a heat treatment. Thus, by subsequently applying a red, green and blue pigmented coating on top of each other with this process a color filter layer can be produced. The color filter systems can be used, for example, for display and image scanner in television receivers, video monitors or computers, in flat panel display technology etc..

In such color filter systems as the red pigment, for instance, an anthraquinone pigment, e.g. C. I. Pigment Red 177 ("C.I." refers to the Color Index, known to the person skilled in the art and publicly available), or a perylene pigment, e.g. C. I. Pigment Red 155, is used either alone or in the form of a mixture with a diazo yellow pigment or an isoindoline type yellow pigment. Especially advantageous is their mixture with C.I. Pigment Yellow 83 or C. I. Pigment Yellow 139.. Further suitable examples for the pigment are such of C.I. Pigment Red 144, 177, 185, 202, 209, 214, 222, 254, 255, 264, 272 and C.I. Pigment Yellow 83, 93, 95, 109, 110, 128, 129, 138, 139, 166. As green pigment, for example, halogenated phthalocyanine type pigments are used either alone or in combination with a diazo yellow pigment or an isoindoline type yellow pigment, for example, a combination of C. I. Pigment Green 7, 36, 136 or 37 and C. I. Pigment Yellow 83 or C.I. Pigment Yellow 139. Examples for suitable blue pigments are phthalocyanine type pigments, used either alone or in combination with an oxazine type violet pigment, for instance, a combination of C. I. Pigment Blue 15:3 and C. I. Pigment Violet 23. Further examples for blue pigments are such of C.I. Blue 15:4, 15:6, 16 and 60. Other suitable pigments are such of C.I. Violet 19, 23, 32, 37, 177 and C.I. Orange 73. Also combinations of two or three pigments are used. Especially suitable in color filter applications are powdery processed pigments prepared by finely dispersing the above mentioned pigments into a resin. Examples of pigments used in the black matrix are, carbon black, titanium black, iron oxide, C.I. Pigment Black 1 and 7, which are used either alone or in combination.

The concentration of the pigment in the total solid component (pigments of various colors and resin) is for example in the range of 10% to 50% by weight, in particular in the range of 20% to 40% by weight.

The compositions according to the invention also find application for the production of one- or more-layered materials for the image recording or image reproduction (copies, reprography), which may be mono- or polychromatic. Furthermore the materials are suitable for color proofing systems. In this technology formulations containing microcapsules can be applied and for the image production the radiation curing can be followed by a thermal treatment. Such systems and technologies and their applications are for example disclosed in US 5376459.

Substrates used for photographic information recordings include, for example, films of polyester, cellulose acetate or polymer-coated papers; substrates for offset printing formes are

pecially treated aluminium, substrates for producing printed circuits are copper-clad laminates, and substrates for producing integrated circuits are silicon wafers. The layer thicknesses for photographic materials and offset printing formes is generally from about 0.5 μm to 10 μm , while for printed circuits it is from 1.0 μm to about 100 μm . Following the coating of the substrates, the solvent is removed, generally by drying, to leave a coat of the photoresist on the substrate.

The term "imagewise" exposure includes both, exposure through a photomask comprising a predetermined pattern, for example a slide, as well as exposure by means of a laser or light beam, which for example is moved under computer control over the surface of the coated substrate and in this way produces an image, and irradiation with computer-controlled electron beams. It is also possible to use masks made of liquid crystals that can be addressed pixel by pixel to generate digital images, as is, for example, described by A. Bertsch, J.Y. Jezequel, J.C. Andre in *Journal of Photochemistry and Photobiology A: Chemistry* 1997, 107, p. 275-281 and by K.-P. Nicolay in *Offset Printing* 1997, 6, p. 34-37.

Following the imagewise exposure of the material and prior to development, it may be advantageous to carry out thermal treatment for a short time. In this case only the exposed sections are thermally cured. The temperatures employed are generally 50-150°C, preferably 80-130°C; the period of thermal treatment is in general between 0.25 and 10 minutes.

The photocurable composition may additionally be used in a process for producing printing plates or photoresists as is described, for example, in DE 4013358. In such a process the composition is exposed for a short time to visible light with a wavelength of at least 400 nm, without a mask, prior to, simultaneously with or following imagewise irradiation.

After the exposure and, if implemented, thermal treatment, the unexposed areas of the photosensitive coating are removed with a developer in a manner known per se.

As already mentioned, the novel compositions can be developed by aqueous alkalis. Particularly suitable aqueous-alkaline developer solutions are aqueous solutions of tetraalkylammonium hydroxides or of alkali metal silicates, phosphates, hydroxides and carbonates. Minor quantities of wetting agents and/or organic solvents may also be added, if desired, to these solutions. Examples of typical organic solvents, which may be added to the developer

liquids in small quantities, are cyclohexanone, 2-ethoxyethanol, toluene, acetone and mixtures of such solvents.

Photocuring is of great importance for printings, since the drying time of the ink is a critical factor for the production rate of graphic products, and should be in the order of fractions of seconds. UV-curable inks are particularly important for screen printing and offset inks.

As already mentioned above, the novel mixtures are highly suitable also for producing printing plates. This application uses, for example, mixtures of soluble linear polyamides or styrene/butadiene and/or styrene/isoprene rubber, polyacrylates or polymethyl methacrylates containing carboxyl groups, polyvinyl alcohols or urethane acrylates with photopolymerizable monomers, for example acrylamides and/or methacrylamides, or acrylates and/or methacrylates, and a photoinitiator. Films and plates of these systems (wet or dry) are exposed over the negative (or positive) of the printed original, and the uncured parts are subsequently washed out using an appropriate solvent or aqueous solutions.

Another field where photocuring is employed is the coating of metals, in the case, for example, of the coating of metal plates and tubes, cans or bottle caps, and the photocuring of polymer coatings, for example of floor or wall coverings based on PVC.

Examples of the photocuring of paper coatings are the colourless varnishing of labels, record sleeves and book covers.

Also of interest is the use of the novel photoinitiators for curing shaped articles made from composite compositions. The composite compound consists of a self-supporting matrix material, for example a glass fibre fabric, or alternatively, for example, plant fibres [cf. K.-P. Mieck, T. Reussmann in *Kunststoffe* 85 (1995), 366-370], which is impregnated with the photocuring formulation. Shaped parts comprising composite compounds, when produced using the novel compounds, attain a high level of mechanical stability and resistance. The novel compounds can also be employed as photocuring agents in moulding, impregnating and coating compositions as are described, for example, in EP 7086. Examples of such compositions are gel coat resins, which are subject to stringent requirements regarding curing activity and yellowing resistance, and fibre-reinforced mouldings, for example, light diffusing panels which are planar or have lengthwise or crosswise corrugation. Techniques for producing such mouldings, such as hand lay-up, spray lay-up, centrifugal casting or filament winding, are described, for example, by P.H. Selden in "Glasfaserverstärkte Kunststoffe", page

610, Springer Verlag Berlin-Heidelberg-New York 1967. Examples of articles which can be produced by these techniques are boats, fibre board or chipboard panels with a double-sided coating of glass fibre-reinforced plastic, pipes, containers, etc. Further examples of moulding, impregnating and coating compositions are UP resin gel coats for mouldings containing glass fibres (GRP), such as corrugated sheets and paper laminates. Paper laminates may be based on urea resins or melamine resins. Prior to production of the laminate, the gel coat is produced on a support (for example a film). The novel photocurable compositions can also be used for casting resins or for embedding articles, for example electronic components, etc..

The compositions and compounds according to the invention can be used for the production of holographies, waveguides, optical switches wherein advantage is taken of the development of a difference in the index of refraction between irradiated and non-irradiated areas.

The use of photocurable compositions for imaging techniques and for the production of information carriers, electronic circuits, plating masks and micromechanical parts is also important. In such applications, as already described above, the layer (wet or dry) applied to the support is irradiated imagewise, e.g. through a photomask, with UV or visible light, and the unexposed areas of the layer are removed by treatment with a developer. Application of the photocurable layer to metal can also be carried out by electrodeposition. The exposed areas are crosslinked and are therefore insoluble in the developer and remain on the support. Appropriate colouration produces visible images. Where the support is a metallized layer, the metal can, following exposure and development, be etched away at the unexposed areas or reinforced by electroplating.

The photosensitivity of the novel compositions can extend in general from about 190 nm to 600 nm. Suitable radiation is present, for example, in sunlight or light from artificial light sources. Consequently, a large number of different types of light sources are employed. Both, point sources and arrays ("lamp carpets") are suitable. Examples are carbon arc lamps, xenon arc lamps, medium-, high- and low-pressure mercury lamps, optionally metal halide doped (metal-halogen lamps), microwave-stimulated metal vapour lamps, excimer lamps, superactinic fluorescent tubes, fluorescent lamps, argon incandescent lamps, electronic flashlights, photographic flood lamps, light emitting diodes (LED), and excimer lasers. Electron beams and X-rays can also be used. The distance between the radiation source

and the substrate to be exposed in accordance with the invention may vary depending on the intended application and the type and power density of the radiation source and the optical path, and may be, for example, from 1 cm to 150 cm. Laser light sources, for example excimer lasers, such as KrF lasers for exposure at 248 nm and ArF lasers at 193 nm are also suitable. Lasers in the visible region can also be employed, for example argon laser, frequency doubled YAG laser. By this method it is possible to produce integrated circuits and printed circuits in the electronics industry, lithographic offset printing plates or relief printing plates, and also photographic image recording materials.

The invention therefore also provides a process for the photopolymerization of monomeric, oligomeric or polymeric compounds containing at least one ethylenically unsaturated double bond, which comprises adding to the above mentioned compounds at least one photoinitiator of the formula I, II, III, IV, V or VI as described above and a coinitiator (c) and irradiating the resulting composition with electromagnetic radiation, in particular light of the wavelength 190 to 600 nm, with e-beam radiation or with X-rays.

The invention additionally provides compositions for producing pigmented and nonpigmented paints and varnishes, powder coatings, printing inks, printing plates, adhesives, dental compositions, resist materials, including photoresists, color filter materials, as composition for encapsulating electrical and electronic components, for producing magnetic recording materials, micromechanical parts, waveguides, optical switches, plating masks, etch masks, colour proofing systems, glass fibre cable coatings, screen printing stencils, for producing three-dimensional objects by means of stereolithography, and as image recording material, especially for holographic recordings, microelectronic circuits, decolorizing materials, decolorizing materials for image recording materials, for image recording materials using microcapsules; and a process for producing pigmented and non-pigmented paints and varnishes, powder coatings, printing inks, printing plates, adhesives, dental compositions, composite compositions, resists, including photoresists, color filter materials, compositions for encapsulating electrical and electronic components, for producing magnetic recording materials, micromechanical parts, waveguides, optical switches, plating masks, etch masks, colour proofing systems, glass fibre cable coatings, screen printing stencils, for producing three-dimensional objects by means of microlithography, plating, stereolithography, for producing image recording materials, especially for holographic recordings, microelectronic cir-

cuits, decolorizing materials, decolorizing materials for image recording materials, for image recording materials using microcapsules.

The invention further provides a coated substrate which is coated on at least one surface with a composition as described above, and further pertains to a process for the production of relief images, in which a coated substrate is subjected to imagewise exposure and then the unexposed portions are removed with a solvent. As "solvent" in this connection not only organic solvents are used, but also and in particular aqueous alkaline developers are employed. Imagewise exposure may be effected by irradiating through a mask or by means of a laser, X-ray or electron beam. Of particular advantage in this context is the laser beam exposure already mentioned above.

The compounds of the invention have a high sensitivity and resolution at low concentration with a coinitiator. They have a good thermal stability and low volatility.

The examples which follow illustrate the invention in more detail. Parts and percentages are, as in the remainder of the description and in the claims, by weight, unless stated otherwise. Where alkyl radicals having more than three carbon atoms are referred to without any mention of specific isomers, the n-isomers are meant in each case.

A) Preparation Examples

Example 1: Preparation of 2-methoxyethyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate

1.1 2-Methoxyethyl phenylglyoxalate

In a flask equipped with a distillation apparatus, 164.2 g (1 mol) of methyl phenylglyoxalate and 49.8 g (0.2 mol) of dibutyltin oxide are added to 400 ml of 2-methoxyethanol and heated to reflux for 16 hours. Methanol is distilled off during this time. Excess 2-methoxy ethanol is subsequently distilled in vacuo to give a crude reaction product which is purified by filtration over silica gel. After evaporation of the solvent, 208 g (100%) of 2-methoxyethyl phenylglyoxalate are obtained as a colorless liquid.

$^1\text{H-NMR}$ (CDCl_3), δ [ppm]: 8.00 (m, 2 aromatic H); 7.63 (m, 1 aromatic H); 7.50 (m, 2 aromatic H); 4.51 (dxd; 2H, COOCH_2 -); 3.69 (dxd, 2H, $-\text{CH}_2\text{-O}-$); 3.39 (s, 3H, CH_3O).

1.2 2-Methoxyethyl α -(hydroxyimino)-2-phenylacetate

61.7 g (0.296 mol) of 2-methoxyethyl phenylglyoxalate are dissolved in 360 ml pyridine. 22.7 g (0.0326 mol) of hydroxylammonium hydrochloride are added in portions to this solution. When the addition is complete, the reaction mixture is stirred at room temperature for 2 hours. After addition of ethyl acetate and water, the organic layer is separated, washed with diluted HCl and water and dried over magnesium sulfate. Evaporation of the solvent gives 68 g (100%) of crude 2-methoxyethyl α -(hydroxyimino)-2-phenylacetate as a slightly brownish liquid. This compound is used without further purification in the next step.

$^1\text{H-NMR}$ (CDCl_3), δ [ppm]: 7.60-7.25 (m, 5 aromatic H); 4.54 and 4.43 (dxd, 2H, trans and cis COOCH_2 -); 3.70 and 3.65 (dxd, 2H, trans and cis $-\text{CH}_2\text{-O}-$); 3.39 (s, 3H, CH_3O). The trans/cis isomer ratio is approximately 3:1.

1.3 2-Methoxyethyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate

A solution of 8.8 g (0.39 mol) of crude 2-methoxyethyl α -(hydroxyimino)-2-phenylacetate and 5.98 g of triethylamine in 65 ml tetrahydrofuran is cooled in an ice bath, and 8.3 g (0.043 mol) of p-toluenesulfonic acid chloride dissolved in 18 ml of tetrahydrofuran are added dropwise over 30 minutes. The resulting suspension is stirred for 16 hours at room temperature and then poured onto ice/water. The mixture is extracted with ethyl acetate, the organic layer washed with diluted HCl and water and dried over magnesium sulfate. Evaporation of the solvent gives an orange oil which is purified by chromatography on silica gel (eluent hexane/ethyl acetate 3:1). 12.68 g (86%) 2-Methoxyethyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate are thus obtained as a colorless liquid. According to $^1\text{H-NMR}$ -analysis, the product is a mixture of 72% of the trans isomer and 28% of the cis isomer.

$^1\text{H-NMR}$ (CDCl_3), δ [ppm]: 7.90 (d, 2 aromatic H); 7.55 (d, 2 aromatic H); 7.5-7.3 (m, 5 aromatic H); 4.55 and 4.38 (dxd, 2H, trans and cis COOCH_2 -); 3.66 and 3.61 (dxd, 2H, trans and cis $-\text{CH}_2\text{-O}-$); 3.38 and 3.36 (s, 3H, CH_3O); 2.42 and 2.40 (s, 3H, $\text{CH}_3\text{-C}_6\text{H}_4$ -).

Elemental analysis: C ₁₈ H ₁₉ NO ₆ S (376.4)	C [%]	H [%]	N [%]	S [%]
calculated	57.28	5.07	3.71	8.49
found	57.27	5.08	3.58	8.54

Example 2: Preparation of hexyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate

2.1 Hexyl phenylglyoxalate

16.42 g (0.1 mol) of methyl phenylglyoxalate is transesterified as described in example 1.1, using 1-hexanol instead of methoxyethanol. 21.33 g (87%) hexyl phenylglyoxalate are obtained as a colorless liquid.

$^1\text{H-NMR}$ (CDCl_3), δ [ppm]: 7.98 (m, 2 aromatic H); 7.64 (m, 1 aromatic H); 7.50-7.45 (m, 2 aromatic H); 4.36 (t, 2H, COOCH_2 -); 1.8-1.65 (m, 2H); 1.50-1.30 (m, 6H); 0.86 (t, 3H).

2.2 Hexyl α -(hydroxyimino)-2-phenylacetate

17.4 g (0.074 mol) of hexyl phenylglyoxalate are reacted with 5.66 g (0.084 mol) of hydroxylammonium hydrochloride as described in example 1.2. Yield: 18.1 g (97%) of crude hexyl α -(hydroxyimino)-2-phenylacetate as a yellowish liquid. This compound is used without further purification in the next step.

$^1\text{H-NMR}$ (CDCl_3), δ [ppm]: 7.60-7.25 (m, 5 aromatic H); 4.38 and 4.27 (t, 2H, trans and cis COOCH_2); 1.85-1.65 (m, 2H); 1.45-1.20 (m, 6H); 0.87 (t, 3H). The trans/cis isomer ratio is approximately 3:1.

2.3 Hexyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate

18.0 g (0.0722 mol) of hexyl α -(hydroxyimino)-2-phenylacetate are reacted with 15.1 g of p-toluenesulfonic acid chloride as described in example 1.3 to give 23.2 g (80%) of hexyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate as a colorless liquid after purification by chromatography. According to $^1\text{H-NMR}$ -analysis, the product is a mixture of 69% of the trans isomer and 31% of the cis isomer.


$^1\text{H-NMR}$ (CDCl_3), δ [ppm]: 7.89 (d, 2 aromatic H); 7.55-7.75 (d and m, 7 aromatic H); 4.38 and 4.24 (t, 2H, trans and cis COOCH_2); 2.43 and 2.41 (s, 3H, $\text{CH}_3\text{-C}_6\text{H}_4$ -); 1.73 (m, 2H); 1.4 - 1.15 (m, 6H); 0.88 (t, 3H)..

Elemental analysis: $\text{C}_{21}\text{H}_{25}\text{NO}_5\text{S}$ (403.5)	C [%]	H [%]	N [%]	S [%]
calculated	62.51	6.25	3.47	7.95
found	62.66	6.34	3.50	8.11

Examples 3-33:

The following examples 3-33 are prepared from the corresponding starting materials as described in examples 1 and 2. If not otherwise indicated, the products are mixtures of isomers with a trans/cis ratio of approximately 7:3. The structures and physical data are collected in table 1.


Table 1:



ex.	R ₇	R ₈	R ₉	R ₃ '	physical properties	Analysis [%]			
						C	H	N	calc. Found S
3	H	H	CH ₃	CH ₃	colorless viscous liquid trans/cis 58:42	46.69 46.81	4.31 4.32	5.44 5.20	12.46 12.33
4	H	H	CH ₃	CH ₃	colorless viscous liquid trans/cis 93:7	46.69 46.97	4.31 4.54	5.44 5.31	12.46 11.23
5	H	H	n-C ₃ H ₇	p-tol*	colorless liquid trans/cis 91:9	59.82 59.81	5.30 5.38	3.88 4.03	8.87 8.90
6	H	H	n-C ₃ H ₇	p-tol*	colorless solid, mp 60- 83°C trans/cis 35:65	59.82 59.79	5.30 5.34	3.88 3.88	8.87 8.88
7	H	H	i-C ₃ H ₇	p-tol*	colorless viscous liquid	59.82 59.89	5.30 5.30	3.88 3.80	8.87 8.86
8	H	H	i-C ₃ H ₇	p-tol*	colorless solid mp. 79- 105°C trans/cis 27:30	59.82 59.89	5.30 5.28	3.88 3.73	8.87 8.95
9	H	H	n-C ₄ H ₉	p-tol*	colorless liquid	60.78 60.92	5.64 5.62	3.73 3.60	8.54 8.47
10	CH ₃	H	C ₂ H ₅	p-tol*	colorless wax	59.82 59.85	5.30 5.50	3.88 3.79	8.87 8.91
11	CH ₃	H	n-C ₃ H ₇	p-tol*	colorless crystals, mp 80- 83°C	60.78 60.68	5.64 5.65	3.73 3.78	8.54 8.55

ex.	R ₇	R ₈	R ₉	R ₃ '	physical properties	Analysis [%] calc. Found			
						C	H	N	S
12	CH ₃	H	n-C ₃ H ₇	CH ₃	colorless solid	60.78 60.68	5.64 5.65	3.73 3.78	8.54 8.55
13	CH ₃	H	n-C ₄ H ₉	p-tol*	colorless viscous liquid	61.68 61.64	5.95 6.00	3.60 3.60	8.23 8.22
14	CH ₃	H	CH ₃ O-C ₂ H ₄	p-tol*	colorless viscous liquid	58.30 58.35	5.41 5.45	3.58 3.63	8.19 8.22
15	C ₂ H ₅	H	C ₂ H ₅	p-tol*	colorless viscous liquid	60.78 60.69	5.64 5.76	3.73 3.79	8.54 8.66
16	C ₂ H ₅	H	C ₂ H ₅	p-tol*	colorless solid mp. 83-86°C cis isomer	60.78 60.56	5.64 5.60	3.73 3.81	8.54 8.59
17	n-C ₄ H ₉	H	C ₂ H ₅	p-tol*	colorless viscous liquid	62.51 62.49	6.25 6.28	3.47 3.70	7.95 7.84
18	n-C ₄ H ₉	H	C ₂ H ₅	CH ₃	colorless liquid	55.03 55.93	6.46 6.89	4.28 4.30	9.79 9.25
19	F	H	C ₂ H ₅	p-tol*	yellowish liquid	55.88 55.54	4.41 4.65	3.83 3.76	8.78 8.91
20	CH ₃ O	H	C ₂ H ₅	p-tol*	viscous yellowish liquid	57.28 57.04	5.07 5.24	3.71 3.75	8.49 8.39
21	CH ₃ O	CH ₃ O	C ₂ H ₅	p-tol*	viscous yellowish liquid	56.01 55.24	5.19 5.32	3.44 3.35	7.87 7.60
22	CH ₃ O	CH ₃ O	CH ₃ O-C ₂ H ₄ -	p-tol*	viscous yellowish liquid	54.91 54.62	5.30 5.94	3.20 2.98	7.33 6.51
23	CH ₃ O	CH ₃ O	CH ₃ O-C ₂ H ₄ -	CH ₃	solid beige trans/cis 95:5	46.53 46.52	5.30 5.24	3.88 3.84	8.87 8.98
24	CH ₃ S	H	CH ₃	p-tol*	yellowish solid, mp. 113-120°C trans/cis 22:78	53.81 53.70	4.52 4.84	3.69 3.64	16.90 16.95
25	CH ₃ S	H	CH ₃	p-tol*	yellowish viscous liquid trans/cis 93:7	53.81 53.80	4.52 4.61	3.69 3.61	16.90 16.92

ex.	R ₇	R ₈	R ₉	R ₃ '	physical properties	Analysis [%]			
						C	H	N	calc. Found S
26	CH ₃ S	H	CH ₃	CH ₃	yellowish solid mp. 72-91°C trans/cis 93:7	43.55 43.63	4.32 4.30	4.62 4.61	21.14 21.43
27	CH ₃ S	H	C ₂ H ₅	p-tol*	yellowish viscous liquid	54.95 55.14	4.87 4.79	3.56 3.55	16.30 16.38
28	CH ₃ S	H	CH ₃ O-C ₂ H ₄ -	p-tol*	yellowish viscous liquid	53.89 54.00	5.00 4.95	3.31 3.36	15.14 15.08
29	CH ₃ S	H	CH ₃ O-C ₂ H ₄ -	CH ₃	yellowish viscous liquid	44.95 45.07	4.93 5.06	4.03 3.91	18.46 18.66
30	n-C ₄ H ₉ S	n-C ₄ H ₉ S	C ₂ H ₅	p-tol*	reddish viscous liquid	57.34 57.64	6.35 6.44	2.67 2.68	18.36 18.44
31	(CH ₃) ₂ N	H	C ₂ H ₅	p-tol*	orange solid mp. 148-151°C	58.45 58.20	5.68 5.87	7.17 7.45	8.21 8.47
32	CH ₃ O	CH ₃ O	C ₂ H ₅	CH ₃	yellowish solid mp. 84-87°C	47.12 46.78	5.17 5.03	4.23 4.11	9.68 9.97
33	CH ₃ S	H	C ₂ H ₅	CH ₃	yellowish solid mp. 51-63°C	45.41 45.37	4.76 4.89	4.41 4.41	20.20 20.22

* p-tol is 

Example 34: Preparation of ethyl α -(4-methylphenylsulfonyloxyimino)-2-(thianthren-2-yl)-acetate

34.1 Ethyl 2-(thianthren-2-yl)- α -keto-acetate

29.3 g (0.22 mol) of AlCl₃ are added portionwise to a solution of 21.6 g (0.1 mol) of thianthrene and 28.7 g (0.21 mol) of ethyl oxalic acid chloride in 150 ml methylenechloride at 0°C. The resulting solution is stirred during two hours at room temperature and subsequently poured onto water. The product is extracted with methylenechloride, the organic solution dried over magnesium sulfate and the solvent evaporated. The residue is purified by chro-

matography on silica gel (eluent: petroleum ether/ethyl acetate 7:1) to give 13 g (41%) of 2-(thianthren-2-yl)- α -keto-acetate as viscous yellowish oil.

$^1\text{H-NMR}$ (CDCl_3), δ [ppm]: 8.08 (d, 1 aromatic H); 7.86 (dxd, 1 aromatic H); 7.55 (d, 1 aromatic H); 7.45 (m, 2 aromatic H); 7.25 (m, 2 aromatic H); 4.43 (q, 2H); 1.39 (t, 3H).

34.2 Ethyl 2-(thianthren-2-yl)- α -(hydroxyimino)-acetate

As described in example 1.2, 7.7 g (0.024 mol) of 2-(thianthren-2-yl)- α -keto-acetate are reacted with 1.85 g (0.0267 mol) of hydroxylammonium hydrochloride in pyridine to give 7.5 g (94%) of crude 2-(thianthren-2-yl)- α -(hydroxyimino)-acetate, which is used without further purification for the next reaction step.

$^1\text{H-NMR}$ (CDCl_3), δ [ppm]: 7.65-7.15 (m 7 aromatic H); 4.44 and 4.35 (q, 2H); 1.37 and 1.33 (t, 3H).

34.3 Ethyl α -(4-methylphenylsulfonyloxyimino)-2-(thianthren-2-yl)-acetate

9.5 g (0.029 mol) of ethyl 2-(thianthren-2-yl)- α -(hydroxyimino)-acetate are reacted with 6.0 g (0.034 mol) of p-toluenesulfonic acid chloride as described in example 1.3 to give, after purification by chromatography (silica gel, eluent white spirit/ethyl acetate 4:1), 8.2 g (59%) of ethyl α -(4-methylphenylsulfonyloxyimino)-2-(thianthren-2-yl)-acetate as a yellow viscous liquid.

Elemental analysis: $\text{C}_{23}\text{H}_{19}\text{NO}_5\text{S}_3$ (485.60):	C [%]	H [%]	N [%]	S [%]
calculated	56.89	3.94	2.88	19.81
found	56.89	4.13	2.96	19.64

Example 35: Methylsulfonyloxyimino-3,4-dimethoxyphenyl acetic acid 2-{2-(methylsulfonyloxyimino-3,4-dimethoxyphenyl-acetoxy)-ethoxy}-ethyl ester

35.1 3,4-Dimethoxy-phenyl)-oxo-acetic acid 2-{2-[(3,4-dimethoxy-phenyl)-oxo-acetoxy]-ethoxy}-ethyl ester

This product is obtained in 45% yield by transesterification of phenylglyoxalate with 2-(2-hydroxy-ethoxy)-ethanol instead of 2-methoxyethanol as described in example 1.1. The crude product is used for the next reaction step without further purification

35.2 Hydroxyimino-3,4-dimethoxyphenyl acetic acid 2-{2-(hydroxyimino-3,4-dimethoxyphenyl-acetoxy)-ethoxy}-ethyl ester

48.0 g (0.1 mol) of (3,4-Dimethoxy-phenyl)-oxo-acetic acid 2-{2-[(3,4-dimethoxy-phenyl)-oxo-acetoxy]-ethoxy}-ethyl ester are transformed into hydroxyimino-3,4-dimethoxyphenyl acetic acid 2-{2-(hydroxyimino-3,4-dimethoxyphenyl-acetoxy)-ethoxy}-ethyl ester by treatment with

14.97 g (0.21 mol) of hydroxylammonium hydrochloride in pyridin as described in example 1.2. 33.25 g (65%) of the crude product are obtained as a beige solid and used in the next reaction step without further purification.

35.3 Methylsulfonyloxyimino-3,4-dimethoxyphenyl acetic acid 2-[2-(methylsulfonyloxyimino-3,4-dimethoxyphenyl-acetoxy)-ethoxy]-ethyl ester

10.4 g (0.02 mol) of Hydroxyimino-3,4-dimethoxyphenyl acetic acid 2-[2-(hydroxyimino-3,4-dimethoxyphenyl-acetoxy)-ethoxy]-ethyl ester are reacted with 5.0 g (0.44 mol) of methylsulfonyl chloride in 100 ml of pyridine as described in example 1.3. After isolation and chromatography on silicagel, 7.1 g (53%) of 2-[2-(methylsulfonyloxyimino-3,4-dimethoxyphenyl-acetoxy)-ethoxy]-ethyl ester are obtained as a sticky yellowish solid. According to the ¹H-NMR spectrum, the product consists of two major trans/cis in a ratio of 3:1 and contains residues of solvent.

¹H-NMR (CDCl₃), δ [ppm]: 7.25 (dxd, 2 aromatic H), 7.10 (dxd, 2 aromatic H); 6.85 (dxd, 2 aromatic H); 4.6 and 4.55 (t, 4 H); 3.89 and 3.88 (s, 12 H, CH₃O); 3.84 (m, 4 H); 3.20 and 3.18 (s, 6H).

Elemental analysis: C₂₆H₃₂N₂O₁₅S₂ (676.67)

	C [%]	H [%]	N [%]	S [%]
calculated	46.15	4.77	4.14	9.48
found	47.18	5.10	4.12	8.27

Example 36: Preparation of N,N-diethyl α-(4-methylphenylsulfonyloxyimino)-2-phenylacetamide

36.1 N,N-diethyl α-keto-2-phenylacetamide

23 g (0.2 mol) of Dichloromethyl-methylether are added dropwise to 30 g (0.2 mol) of phenylglyoxylic and the resulting suspension is stirred for 2 hours. The yellowish solution is then cooled in an ice bath, and 44 g (0.6 mol) of diethylamine are added dropwise while stirring. The reaction mixture is stirred overnight, poured on water/ice and extracted with dichloromethane. The organic solution is washed with diluted HCl, dried over magnesium sulfate and the solvent is evaporated. The resulting reddish liquid is filtered over silicagel (eluent: hexane/ethyl acetate 3:1) to give 39.8 g (97%) of N,N-diethyl α-keto-2-phenylacetamide as a yellowish liquid after evaporation of the solvent. The crude product is used without further purification in the next step.

Elemental analysis: C ₁₂ H ₁₅ NO ₂ (205.26):	C [%]	H [%]	N [%]
calculated	70.22	7.37	6.82
found	69.40	7.47	6.15

36.2 N,N-diethyl α -(hydroxyimino)-2-phenylacetylamine

26.0 g (0.126 mol) of N,N-diethyl α -keto-2-phenylacetylamine and 9.6 g (1.39 mol) of hydroxylamine-hydrochloride are dissolved in 250 ml of pyridine and the resulting solution is stirred at room temperature for 12 hours and subsequently heated to 60°C for another 6 hours. After cooling to room temperature, ethyl acetate and water are added, the organic layer is separated and washed several times with diluted HCl and water. After drying and evaporation of the solvent, 25.9 g (93%) of crude N,N-diethyl α -(hydroxyimino)-2-phenylacetylamine are obtained as a sticky yellowish solid.

¹H-NMR (CDCl₃), δ [ppm]: 7.65-7.50 (m, 2 aromatic H); 7.40-7.25 (m, 3 aromatic H); 3.56 (q, 2H); 3.20 (q, 2H); 1.24 (t, 3H); 1.03 (t, 3H).

36.3 N,N-diethyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetylamine


11.44 g (0.06 mol) of p-toluenesulfonic acid chloride dissolved in 25 ml of tetrahydrofuran (THF) are dropwise added to a solution of 12 g (0.055 mol) of α -(hydroxyimino)-2-phenylacetylamine and 8.3 g (0.082 mol) of triethylamine in 90 ml of THF at 0°C. When the addition is complete, the reaction mixture is stirred at 0°C for another hour and then at room temperature over night. Ethyl acetate and water are added to the mixture, the organic layer is separated and washed several times with diluted HCl and water. The solution is dried over magnesium sulfate, the solvent evaporated and the remaining red oil purified by chromatography on silica gel (eluent: petroleum ether/ethyl acetate 4:1). 10.57 g (52%) of N,N-diethyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetylamine are thus obtained as a colorless solid, mp. 73-75°C.

Elemental analysis: C ₁₉ H ₂₂ N ₂ O ₄ S (374.5)	C [%]	H [%]	N [%]	S [%]
calculated	60.94	5.92	7.48	8.56
found	61.01	6.02	7.36	8.60

Examples 37-39:

The following examples 37-39 are prepared from the corresponding starting materials as described in example 36. The structures and physical data are listed in table 2.

Table 2:



ex.	R ₇	R ₃ '	R ₉	R ₉ '	physical properties	Analysis [%]			
						C	H	N	calc. Found S
37	H	CH ₃	C ₂ H ₅	C ₂ H ₅	colorless solid, mp. 91-96°C	52.33 52.38	6.08 6.29	9.39 9.16	10.75 10.68
38	H	p-tol*	C ₄ H ₉	C ₄ H ₉	yellowish solid, mp. 68-72°C	64.16 64.43	7.02 7.17	6.51 6.43	7.45 7.16
39	C ₂ H ₅	p-tol*	C ₂ H ₅	C ₂ H ₅	yellowish viscous liquid	62.66 62.61	6.51 6.47	6.96 6.87	7.97 8.06

* p-tol is

Example 40: Preparation of methyl α-(diethoxyphosphoryloxyimino)-2-phenylacetate

40.1 Methyl α-(hydroxyimino)-2-phenylacetate

41.0 g (0.25 mol) of methyl phenylglyoxalate are dissolved in 300 ml of pyridine. 19.1 g (0.27 mol) of hydroxylammonium hydrochloride are added in portions to this solution. When the addition is complete, the reaction mixture is stirred at room temperature for 20 hours. After addition of ethyl acetate and water, the organic layer is separated, washed with diluted HCl and water and dried over magnesium sulfate. Evaporation of the solvent gives 45 g (100%) of crude methyl α-(hydroxyimino)-2-phenylacetate as a slightly brownish liquid. This compound is used without further purification in the next reaction step.

¹H-NMR (CDCl₃), δ [ppm]: 7.55-7.30 (m, 5 aromatic H); 3.96 and 3.87 (s, 3H, CH₃O of the trans and cis isomers). The trans/cis isomer ratio is approximately 3:1.

40.2 Methyl-α-(diethoxyphosphoryloxyimino)-2-phenylacetate

25.1 g (0.14 mol) of Methyl α-(hydroxyimino)-2-phenylacetate, 14.2 g (0.14 mol) of triethylamine and a catalytic amount of 4-dimethylaminopyridine are dissolved in 300 ml of CH₂Cl₂. 24.16 g (0.14 mol) of diethylchlorophosphate are added dropwise to the resulting solution with stirring. The reaction mixture is stirred overnight and subsequently poured on ice/water.

The resulting suspension is extracted with dichloromethane and the organic solution dried over magnesium sulfate. Evaporation of the solvent gives an oil, which is further purified by flash chromatography (silicagel, eluent petroleum ether/ethyl acetate 2:1). 10.5 g (24%) of α -(diethoxyphosphoryloxyimino)-2-phenylacetate are thus obtained as a slightly yellowish liquid.

^{31}P -NMR (CDCl_3), δ [ppm], reference H_3PO_4 : -0.11 and -0.66 ppm (P of the *cis* and *trans* isomers).

Elemental analysis: $\text{C}_{13}\text{H}_{18}\text{NO}_6\text{P}$ (315.27)	C [%]	H [%]	N [%]
calculated	49.53	5.75	4.44
found	49.72	5.98	4.60

Examples 41-44:

The following examples 41-44 are prepared from the corresponding starting materials as described for examples 40. The structures and physical data are given in table 3.

If not otherwise indicated, the products are mixtures of isomers with a *trans/cis* ratio of approximately 7:3.





Table 3:

ex.	R_7	R_8	R_9	R_{14}	physical properties	Analysis [%]			
						C	H	N	calc. Found S
41	H	H	C_3H_7	OC_2H_5	colorless liquid	52.48	6.46	4.08	-
						52.51	6.61	4.11	-
42	CH_3O	CH_3O	$\text{CH}_3\text{O}-\text{C}_2\text{H}_4\text{O}-$	OC_2H_5	viscous yellowish liquid	49.36	6.21	3.60	-
						49.36	6.16	3.49	-
43	CH_3S	H	C_2H_5	OC_2H_5	yellowish liquid	48.00	5.91	3.73	8.54
						48.03	6.09	3.65	8.78
44	H	H	C_3H_7	tol*	yellowish resin	68.96	6.02	3.22	-
						68.68	6.10	3.25	-
45	CH_3S	H	CH_3	OC_2H_5	viscous yellowish liquid	46.54	5.58	3.88	8.87
						46.35	5.72	3.80	8.54
46	CH_3S	H	$\text{CH}_3\text{O}-\text{C}_2\text{H}_4-$	OC_2H_5	viscous yellowish liquid	47.40	5.97	3.46	7.91
						47.08	6.10	3.55	7.64



B) Application Examples





Example 47:

Preparation of Poly(benzylmethacrylate-co-methacrylic acid)

24 g of benzylmethacrylate, 6 g of methacrylic acid and 0.525 g of azobisisobutyronitrile (AIBN) are dissolved in 90 ml of propylene glycol 1-monomethyl ether 2-acetate (PGMEA). The resulting reaction mixture is placed in a preheated oil bath at 80°C. After stirring for 5 hours at 80°C under nitrogen, the resulting viscous solution is cooled to room temperature and used without further purification. The solid content is about 25%.




In the following application examples the photoinitiators collected in table 4 and the coinitiators collected in table 5 are employed.

Table 4: Photoinitiators evaluated

Photoinitiator No.	Structure
P-1	
P-2	
P-3	
P-4	

Photoinitiator No.	Structure
P-5	<chem>CC(=O)S(=O)(=O)ON=C(C#N)C=Cc1ccccc1</chem>
P-6	<chem>CC(=O)S(=O)(=O)ON=C(C#N)C(=O)C=Cc1ccccc1</chem>
P-7	<chem>CC(=O)S(=O)(=O)ON=C1C=CC=C1SC(=C(C#N)C2=CC=CC=C2C)C2=CC=CC=C2</chem>
P-8	<chem>CCOP(=O)(OC)ON=C1C=CC=C1SC(=C(C#N)C2=CC=CC=C2C)C2=CC=CC=C2</chem>
P-9	<chem>c1ccccc1P(=O)(c2ccccc2)ON=C1C=CC=C1SC(=C(C#N)C2=CC=CC=C2C)C2=CC=CC=C2</chem>
P-10 compound of example 1	<chem>CC1=CC=C(C=C1)S(=O)(=O)ON=C(C#N)C(=O)OC2CCOC2=O</chem>
P-11 compound of example 2	<chem>CC1=CC=C(C=C1)S(=O)(=O)ON=C(C#N)C(=O)OC2CCCCC2=O</chem>
P-12 compound of example 40	<chem>CCOP(=O)(OC)ON=C(C#N)C(=O)OC2CCOC2=O</chem>

Table 5: Coinitiators applied

No.	Structure
C-1	4,4'-Bis(diethylamino)-benzophenone 
C-2	Coumarin 106 
C-3	N-Phenylglycine 

Example 48:

A photocurable composition is prepared by mixing the following components:

200.0 parts by weight of a copolymer of benzylmethacrylate and methacrylic acid
 (benzylmethacrylate : methacrylic acid = 80 : 20 by weight)
 25% propylene glycol 1-monomethyl ether 2-acetate
 (PGMEA) solution, prepared in above example 47

50.0 parts by weight of dipentaerythritol hexaacrylate ((DPHA), provided by UCB
 Chemicals),

2.0 parts by weight of the photoinitiator,

1.2 parts by weight of the coinitiator, and


150.0 parts by weight of PGMEA

All operations are carried out under yellow light. The compositions are applied to an aluminum plate using an electric applicator with a wire wound bar. The solvent is removed by heating at 100°C for 2 minutes in a convection oven. The thickness of the dry film is approximately 2 µm. To this coating an acetate film is applied, over which a standardized test negative with 21 steps of different optical density (Stouffer step wedge) is placed. The sample is covered with a second UV-transparent film and pressed onto a metal plate by means of vacuum. Exposure is carried out in a first test series for 5 seconds, in a second series for 10 seconds and in a third series for 20 seconds, using a 3 kW metal halide lamp (ORC, model SMX 3000) at a distance of 60 cm. After exposure, the cover films and the mask are removed and the exposed film is developed with 1% sodium carbonate aqueous solution for 200

sec. at 30°C by using a spray type developer (Walter Lemmen, model T21). The sensitivity of the initiator system used is characterized by indicating the highest number of the steps which completely remain (i.e. polymerize) after developing. The higher the number of steps, the more sensitive is the tested system. The used photoinitiators and coinitiators as well as the results are collected in table 6.

Table 6: Test results example 48

Photoinitiator	Coinitiator	Sensitivity - number of cured steps after		
		5 sec	10 sec	20 sec
P-3	C-1	4	7	9
P-3	C-2	5	8	11
P-4	C-1	7	9	11
P-6	C-1	6	8	10
P-7	C-1	7	9	11
P-7	C-2	6	8	10
P-8	C-1	5	7	9
P-9	C-1	6	8	10
P-12	C-1	3	6	9
P-13	C-1	8	11	13



Example 49:

The photosensitive composition used in example 48 is applied for the following sensitivity test. All operations are carried out under yellow light. The compositions are applied to an aluminum plate using an electric applicator with a wire wound bar. The solvent is removed by heating at 100°C for 2 minutes in a convection oven. The thickness of the dry film is approximately 2 µm. To this coating an acetate film is applied, over which a standardized test negative with 21 steps of different optical density (Stouffer step wedge) is placed. The sample is covered with a second UV-transparent film and pressed onto a metal plate by means of vacuum. Interference filters are placed on the top to select the wavelengths at 365 nm, 405 nm, and 436 nm. Exposure is carried out using a 3 kW metal halide lamp (ORC, model SMX 3000) at a distance of 60 cm. After exposure, the cover films and the mask are removed and the exposed film is developed with 1% sodium carbonate aqueous solution for 200

sec. at 30°C by using a spray type developer (Walter Lemmen, model T21). The sensitivity of the initiator system used is characterized by the minimum dose required to cure upon irradiation at each wavelength, which is calculated from the transmittance of the step with the highest number that is cured. The smaller the dose, the more sensitive is the tested initiator system at the selected wavelength. The used initiator system as well as the results are collected in table 7

Table 7: Test results example 49

Photoinitiator	Coinitiator	Sensitivity [mJ/cm ²]		
		at 365 nm	at 405-nm	at 436 nm
P-1	C-1	26	76	463
P-2	C-1	26	76	463
P-3	C-1	36	151	463
P-3	C-2	73	151	463
P-3	C-3	18	151	>650
P-4	C-1	13	19	82
P-5	C-1	103	214	>650
P-6	C-1	18	38	116
P-7	C-1	18	54	163
P-7	C-2	36	38	58
P-8	C-1	26	54	82
P-9	C-1	18	54	82
P-10	C-1	52	107	463
P-11	C-1	52	151	463
P-12	C-1	73	107	463
P-13	C-1	9	19	82

Example 50:

A photocurable composition is prepared by mixing the following components:

100.0 parts by weight of IRR222 (water soluble urethane

acrylate/DTMPTA^{*1}/TPGDA^{*2}=80/11/9, provided by Daicel UCB)

0.5 parts by weight of the photoinitiator

0.5 parts by weight of the coinitiator C-1

33.3 parts by weight of acetone

^{*1} DTMPTA is di(trimethylolpropane) tetraacrylate

^{*2} TPGDA is tri(propylene glycol) diacrylate

The compositions are applied to an aluminum plate using an electric applicator with a wire wound bar. The solvent is removed by heating at 60°C for 15 minutes in a convection oven.

The thickness of the dry film is approximately 30 μm . To this coating an acetate film is applied, over which a standardized test negative with 21 steps of different optical density (Stouffer step wedge) is placed. The sample is covered with a second UV-transparent film and pressed onto a metal plate by means of vacuum. Exposure is carried out in a first test series for 5 seconds, in a second series for 10 seconds and in a third series for 20 seconds, using a 3 kW metal halide lamp (ORC, model SMX 3000) at a distance of 60 cm. After exposure, the cover films and the mask are removed and the exposed film is developed with water for 15 sec. at 30°C by using a spray type developer (Walter Lemmen, model T21). The sensitivity of the initiator system used is characterized by indicating the highest number of the steps which completely remain (i.e. polymerize) after developing. The higher the number of steps, the more sensitive is the system tested. The tested initiator/coinitiator as well as the test results are collected in table 8.

Table 8: Test results example 50







Photoinitiator	Sensitivity		
	5 sec	10 sec	20 sec
P-1	4	6	8
P-2	4	6	8
P-3	3	5	7
P-4	4	5	7

What is claimed is

1. A radically photopolymerizable composition comprising

(a) at least one ethylenically unsaturated photopolymerizable compound,

(b) as photoinitiator, at least one compound of the formula I, II, III, IV, V and/or VI



wherein

m is 0 or 1;

n is 0, 1, 2 or 3;

x is 1 or 2;

R₁ is phenyl, phenyl which is substituted by one or more of the radicals C₁-C₁₂alkyl, C₁-C₄-haloalkyl, halogen, phenyl, OR₁₀, NR₁₁R₁₂, SR₁₃ and/or -S-phenyl, it being possible for the substituents OR₁₀, SR₁₃ and NR₁₁R₁₂ to form 5- or 6-membered rings, *via* the radicals R₁₀, R₁₁, R₁₂ and/or R₁₃, with further substituents on the phenyl ring or with one of the carbon atoms of the phenyl ring,

or **R₁** is naphthyl, anthracyl or phenanthryl, the radicals naphthyl, anthracyl and phenanthryl being unsubstituted or substituted by C₁-C₆alkyl, phenyl, OR₁₀, NR₁₁R₁₂, SR₁₃ and/or -S-phenyl, it being possible for the substituents OR₁₀, SR₁₃ and NR₁₁R₁₂ to form 5- or 6-membered rings, *via* the radicals R₁₀, R₁₁, R₁₂ and/or R₁₃ with further substituents on the


naphthyl, anthracyl or phenanthryl ring or with one of the carbon atoms of the naphthyl, anthracyl or phenanthryl ring,

or R_1 is a heteroaryl radical which is unsubstituted or substituted by C_1 - C_6 alkyl, phenyl, OR_{10} , $NR_{11}R_{12}$, SR_{13} and/or -S-phenyl, it being possible for the substituents OR_{10} , SR_{13} and $NR_{11}R_{12}$ to form 5- or 6-membered rings, via the radicals R_{10} , R_{11} , R_{12} and/or R_{13} with further substituents on the heteroaryl ring or with one of the carbon atoms of the heteroaryl ring; or R_1 is C_2 - C_{12} alkenyl, C_4 - C_8 cycloalkenyl, or C_6 - C_{12} bicycloalkenyl,

or, if m is zero, R_1 in the formula I additionally is benzoyl, 2-furoyl, 2-thiophenecarbonyl, 2-pyridinecarbonyl or 2-pyrrolecarbonyl, wherein the radicals benzoyl, 2-furoyl, 2-thiophenecarbonyl, 2-pyridinecarbonyl or 2-pyrrolecarbonyl are unsubstituted or substituted by one or more of the radicals C_1 - C_{12} alkyl, C_1 - C_4 haloalkyl, halogen, phenyl, OR_{10} , $NR_{11}R_{12}$, SR_{13} and/or -S-phenyl, it being possible for the substituents OR_{10} , SR_{13} and $NR_{11}R_{12}$ to form 5- or 6-membered rings, via the radicals R_{10} , R_{11} , R_{12} and/or R_{13} , with further substituents on the benzoyl, 2-furoyl, 2-thiophenecarbonyl, 2-pyridinecarbonyl or 2-pyrrolecarbonyl ring or with one of the carbon atoms of the benzoyl, 2-furoyl, 2-thiophenecarbonyl, 2-pyridinecarbonyl or 2-pyrrolecarbonyl ring;

or, if m is zero, n is 1 and simultaneously R_5 is phenyl which is unsubstituted or substituted by one or more C_1 - C_{12} alkyl, C_1 - C_4 haloalkyl, halogen, phenyl, OR_{10} , $NR_{11}R_{12}$, SR_{13} and/or -S-phenyl, R_1 in formula I additionally is hydrogen;

or, if m is 0 and n is 0, R_1 in formula I additionally is CN, hydrogen or C_1 - C_{12} alkyl, with the proviso that R_1 and R_2 are not simultaneously hydrogen or alkyl;

R'_1 is C_2 - C_{12} alkylene, phenylene, naphthylene, , diphenylene or



oxydiphenylene, these radicals are unsubstituted or substituted by C_1 - C_{12} alkyl;

R_2 has one of the meanings of R_1 or is phenyl, CN-substituted phenyl, C_2 - C_6 alkanoyl, benzoyl which is unsubstituted or substituted by C_1 - C_6 alkyl, phenyl, OR_{10} , SR_{13} , $NR_{11}R_{12}$ and/or -S-phenyl, or R_2 is CN, phenoxycarbonyl, NO_2 , C_1 - C_4 haloalkyl, C_2 - C_6 alkoxycarbonyl, $S(O)_y$ - C_1 - C_6 alkyl, $S(O)_y$ - C_6 - C_{12} aryl, C_1 - C_{12} alkyl-substituted $S(O)_y$ - C_6 - C_{12} aryl, SO_2O - C_1 - C_6 alkyl, SO_2O - C_6 - C_{10} aryl, diphenylphosphinoyl or $NHCONH_2$,


or, if m is 1, R_1 and R_2 together with the CO group may form a 5- or 6-membered ring which is unsubstituted or substituted by C_1 - C_6 alkyl, phenyl, OR_{10} , SR_{13} , $NR_{11}R_{12}$ and/or -S-phenyl, said ring may additionally be interrupted by -O-, -S-, -N(R_{11})- and/or by CO, and to said ring may be fused one or more benzo radicals;

y is 1 or 2;


R_3 if x is 1 is C_1 - C_{18} alkylsulfonyl, phenyl- C_1 - C_3 alkylsulfonyl, camphorylsulfonyl, C_1 - C_{10} haloalkylsulfonyl, phenylsulfonyl, naphthylsulfonyl, anthracylsulfonyl or phenanthrylsulfonyl, wherein the groups phenyl, naphthyl, anthracyl and phenanthryl of the radicals phenyl- C_1 - C_3 alkylsulfonyl, phenylsulfonyl, naphthylsulfonyl, anthracylsulfonyl and phenanthrylsulfonyl are unsubstituted or substituted by one or more halogen, C_1 - C_4 haloalkyl, CN, NO_2 , C_1 - C_{16} alkyl, phenyl, C_1 - C_4 alkylthio, OR_{10} , $COOR_{13}$, C_1 - C_4 alkyl-OCO-, $R_{13}OSO_2$ - and/or



R_3 if x is 2, is C_2 - C_{12} alkylenedisulfonyl, phenylenedisulfonyl, naphthylenedisulfonyl,



wherein the groups phenylene, naphthylene, $\text{---} \text{C}_6\text{H}_4 \text{---} CH_2 \text{---} \text{C}_6\text{H}_4 \text{---}$, diphenylene and oxydiphenylene of the radicals phenylenedisulfonyl, naphthylenedisulfonyl,




unsubstituted or substituted by C_1 - C_{12} alkyl;


R_4 and R_5 are independently of each other hydrogen, halogen, C_1 - C_8 alkyl, C_1 - C_6 alkoxy, C_1 - C_4 haloalkyl, CN, NO_2 , C_2 - C_6 alkanoyl, benzoyl, phenyl, -S-phenyl, OR_{10} , SR_{13} , $NR_{11}R_{12}$, C_2 - C_6 alkoxycarbonyl, phenoxycarbonyl, $S(O)_yC_1$ - C_6 alkyl, $S(O)_yC_6$ - C_{12} aryl, C_1 - C_{12} alkyl-substituted $S(O)_yC_6$ - C_{12} aryl, SO_2O - C_1 - C_6 alkyl, SO_2O - C_6 - C_{10} aryl or $NHCONH_2$, or R_4 and R_5 together are a direct bond or $-C(R_{21})=C(R_{22})-C(R_{23})=C(R_{24})-$;

R_6 , R_7 , R_8 independently of one another are hydrogen, $R_{26}Y-$, phenyl optionally substituted by C_1 - C_4 alkyl or C_1 - C_4 alkyl- Y ; or R_6 , R_7 and R_8 are C_1 - C_8 alkyl optionally substituted by halogen, OH, OR_{25} , $COOR_{25}$, or C_1 - C_4 -alkyl-COO-, or optionally interrupted by one or more O-;

or R_6 and R_7 together with the atoms to which they are bound form a 5- or 6-membered saturated or unsaturated ring which is unsubstituted or substituted by one or more C_1 - C_4 alkyl and which ring optionally is interrupted by one or more Y or to which ring other rings are condensed;

R_9 is C_5 - C_8 cycloalkyl, phenyl, optionally substituted by C_1 - C_4 alkyl; or is C_1 - C_{12} alkyl, optionally substituted by halogen, OH, or OR_{25} , or optionally interrupted by one or more -O-;

A is -S-, -O-, - NR_{10} -, or a group of formula A1, A2, A3 or A4  (A1),



Q is C_1 - C_8 -alkylene optionally interrupted by one or more -O-;

X is -O- or - NR_9 -

Y, Y_1 , Y_2 and Y_3 independently of one another are -O- or -S-;

Z is - CR_{28} - or -N-; and

Z_1 is - CH_2 -, -S-, -O- or - NR_{10} -;

R_{10} is hydrogen, phenyl, C_1 - C_{12} alkyl which is unsubstituted or substituted by phenyl, OH, C_1 - C_{12} alkoxy, C_1 - C_{12} alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or by C_2 - C_6 -alkanoyl or R_{10} is C_2 - C_{12} alkyl interrupted by one or more -O-, said interrupted C_2 - C_{12} alkyl is unsubstituted or substituted by phenyl, OH, C_1 - C_{12} alkoxy, C_1 - C_{12} alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or by C_2 - C_6 alkanoyl;

R_{11} and R_{12} independently of one another are hydrogen, C_1 - C_{12} alkyl which is unsubstituted or substituted by OH, C_1 - C_4 alkoxy, C_1 - C_{12} alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or C_1 - C_6 alkanoyl; or R_{11} and R_{12} are C_2 - C_{12} alkyl interrupted by one or more -O-, said interrupted C_2 - C_{12} alkyl is unsubstituted or substituted by OH, C_1 - C_4 alkoxy, C_1 - C_{12} alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or C_1 - C_6 alkanoyl; or R_{11} and R_{12} are phenyl, C_2 - C_6 alkanoyl, benzoyl, C_1 - C_6 alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl, naphthylsulfonyl, anthracylsulfonyl or phenanthrylsulfonyl, or R_{11} and R_{12} , together with the nitrogen atom to which they are bonded, form a 5-, 6- or 7-membered ring which may be interrupted by -O- or by - NR_{10} -;

R_{13} is C_1 - C_{12} alkyl which is unsubstituted or substituted by OH and/or C_1 - C_4 alkoxy or R_{13} is C_2 - C_{12} alkyl interrupted by one or more -O-, said interrupted C_2 - C_{12} alkyl is unsubstituted or substituted by OH and/or C_1 - C_4 alkoxy;

R_{14} and R_{15} independently of one another are C_1 - C_6 alkyl which is unsubstituted or substituted by halogen or phenyl or R_{14} and R_{15} are phenyl which is unsubstituted or substituted by C_1 - C_4 alkyl or halogen;

R_{16} and R_{17} independently of one another have one of the meanings of R_{14} , or R_{16} and R_{17} together are 1,2-phenylene or C_2 - C_6 alkylene which is unsubstituted or substituted by C_1 - C_4 alkyl or halogen;

R_{18} , R_{19} and R_{20} independently of each other are C_1 - C_6 alkyl which is unsubstituted or substituted by halogen, or R_{18} , R_{19} and R_{20} are phenyl which is unsubstituted or substituted by C_1 - C_4 alkyl or halogen, or R_{19} and R_{20} together are 2,2'-biphenylene or C_2 - C_6 alkylene which is unsubstituted or substituted by C_1 - C_4 alkyl or halogen;

R_{21} , R_{22} , R_{23} and R_{24} independently of each other are hydrogen, C_1 - C_4 alkyl, halogen, phenyl, OR_{10} , SR_{13} , $NR_{11}R_{12}$, -S-phenyl, C_2 - C_6 alkoxycarbonyl, phenoxycarbonyl, CN, NO_2 , C_1 - C_4 haloalkyl, $S(O)_yC_1$ - C_6 alkyl, $S(O)_yC_6$ - C_{12} aryl, C_1 - C_{12} alkyl-substituted $S(O)_yC_6$ - C_{12} aryl, SO_2O - C_1 - C_6 alkyl, SO_2O - C_6 - C_{10} aryl or $NHCONH_2$;

R_{25} is C_1 - C_8 alkyl optionally substituted by halogen, OH, or C_1 - C_4 -alkoxy or optionally interrupted by one or more -O-;

R_{26} is phenyl, optionally substituted by C_1 - C_4 alkyl or C_1 - C_4 alkyl-Y; or is C_1 - C_8 alkyl optionally substituted by halogen, OH, OR_{25} , $COOR_{25}$, or C_1 - C_4 alkyl-COO-, or optionally interrupted by one or more -O-;

R_{27} and R_{28} independently of one another have one of the meanings given for R_4 , or R_{27} and R_{28} together are $-CO-NR_{10}CO-$, or $-C(R_{21})=C(R_{22})-C(R_{23})=C(R_{24})-$; and

(c) at least one coinitiator:


2. A composition according to claim 1, wherein the compound of formula I, II, III, IV, V and VI,

R_3 if x is 1 is C_1 - C_{18} alkylsulfonyl, phenyl- C_1 - C_3 alkylsulfonyl, camphorylsulfonyl, C_1 - C_{10} haloalkylsulfonyl, phenylsulfonyl, naphthylsulfonyl, anthracylsulfonyl or phenanthrylsulfonyl, wherein the groups phenyl, naphthyl, anthracyl and phenanthryl of the radicals phenyl- C_1 - C_3 alkylsulfonyl, phenylsulfonyl, naphthylsulfonyl, anthracylsulfonyl and phenanthrylsulfonyl are unsubstituted or substituted by one or more halogen, C_1 - C_4 haloalkyl,


CN, NO₂, C₁-C₁₆alkyl, phenyl, C₁-C₄alkylthio, OR₁₀, COOR₁₃, C₁-C₄alkyl-OCO-, R₁₃OSO₂-

and/or -NR₁₁R₁₂; or R₃ is a group $\begin{array}{c} \text{Y}_1 \\ || \\ -\text{P}-\text{R}_{14} \\ | \\ \text{R}_{15} \end{array}$, $\begin{array}{c} \text{Y}_1 \\ || \\ -\text{P}-\text{R}_{14} \\ | \\ \text{Y}_2-\text{R}_{16} \end{array}$, $\begin{array}{c} \text{Y}_1 \\ || \\ -\text{P}-\text{Y}_3-\text{R}_{17} \\ | \\ \text{Y}_2-\text{R}_{16} \end{array}$;

R₃ if x is 2 is C₂-C₁₂alkylenedisulfonyl, phenylenedisulfonyl, naphthylenedisulfonyl,



wherein the groups phenylene, naphthylene, $\text{---}\text{C}_6\text{H}_4\text{---CH}_2\text{---C}_6\text{H}_4\text{---}$, diphenylene and oxydiphenylene of the radicals phenylenedisulfonyl, naphthylenedisulfonyl,



unsubstituted or substituted by C₁-C₁₂alkyl; and

Y₁, Y₂ and Y₃ independently of each other are -O- or -S-.

3. A composition according to claim 1, wherein component (b) is a compound of formula I, II or III, wherein m is zero.

4. A composition according to claim 1, wherein component (b) is a compound of formula I, III, V or VI wherein

n and m independently of one another are 0 or 1;


x is 1;

R₁ is phenyl which unsubstituted or substituted once or twice by C₁-C₄alkyl, halogen, OR₁₀ or SR₁₃;

R₁' is phenylene;

R₂ is C₂-C₆alkoxycarbonyl, or CN;

R_3 is C_1 - C_8 alkylsulfonyl, or phenylsulfonyl, wherein the group phenyl of the radical phenylsulfonyl is unsubstituted or substituted by C_1 - C_8 alkyl or OR_{10} ; or R_3 is a group,



R_4 and R_5 independently of one another are hydrogen or C_1 - C_8 alkyl;

R_6 is hydrogen;

R_{12} is hydrogen or C_1 - C_4 alkyl;

R_{10} and R_{13} independently of one another are C_1 - C_4 alkyl;

A is -S-;

Y_1 , Y_2 and Y_3 are -O-;

X is -O- or - NR_9 ;

Q is C_1 - C_8 -alkylene optionally interrupted by -O-;

R_{14} and R_{15} independently of one another are phenyl or C_1 - C_4 alkyl-substituted phenyl;

R_{16} and R_{17} independently of one another are C_1 - C_4 alkyl.

5. A photopolymerizable composition according to claim 1, comprising as coinitiator (c) a compound selected from the group consisting of benzophenone derivatives, thioxanthone derivatives or coumarin derivatives.


6. A photopolymerizable composition according to claim 1, comprising additionally at least one binder polymer (d).

7. A photopolymerizable composition according to claim 6, comprising as binder polymer (d), a copolymer of methacrylate and methacrylic acid.

8. A photopolymerizable composition according to claim 1, comprising in addition to the photoinitiator (b) at least one further photoinitiator (e), and/or other additives (f).


9. A photopolymerizable composition according to claim 1 or 8, comprising 0.05 to 20 % by weight of the photoinitiator (b), or the photoinitiators (b) and (e), based on the solid composition.

10. A compound of formula V or VI



wherein

R_3 is C_1 - C_{18} alkylsulfonyl, phenyl- C_1 - C_3 alkylsulfonyl, camphorylsulfonyl, C_1 - C_{18} haloalkylsulfonyl, phenylsulfonyl, naphthylsulfonyl, anthracylsulfonyl or phenanthrylsulfonyl, wherein the groups phenyl, naphthyl, anthracyl and phenanthryl of the radicals phenyl- C_1 - C_3 alkylsulfonyl, phenylsulfonyl, naphthylsulfonyl, anthracylsulfonyl and phenanthrylsulfonyl are unsubstituted or substituted by one or more halogen, C_1 - C_4 haloalkyl, CN, NO_2 , C_1 - C_{16} alkyl, phenyl, C_1 - C_4 alkylthio, OR_{10} , $COOR_{13}$, C_1 - C_4 alkyl- OCO -, $R_{13}OSO_2$ - and/or $-NR_{11}R_{12}$; or R_3 is C_2 - C_6 haloalkanoyl, halobenzoyl, or a group



R_6 , R_7 , R_8 independently of each other are hydrogen, $R_{26}Y$ -, phenyl optionally substituted by C_1 - C_4 alkyl or C_1 - C_4 alkyl- Y -; or R_6 , R_7 and R_8 are C_1 - C_8 alkyl optionally substituted by halogen, OH, OR_{25} , $COOR_{25}$, or C_1 - C_4 -alkyl- COO -, or optionally interrupted by one or more -O-;

or R_6 and R_7 together with the atoms to which they are bound form a 5- or 6-membered saturated or unsaturated ring which is unsubstituted or substituted by one or more C_1 - C_4 alkyl and which ring optionally is interrupted by one or more Y or to which ring other rings are condensed;

Q is C_1 - C_8 -alkylene optionally interrupted by one or more -O-;

X is -O- or $-NR_9$ -;

Y , Y_1 , Y_2 and Y_3 independently of each other are -O- or -S-;

R_9 is C_5 - C_8 cycloalkyl, phenyl, optionally substituted by C_1 - C_4 alkyl; or is C_1 - C_{12} alkyl, optionally substituted by halogen, OH, or OR_{25} , or optionally interrupted by one or more -O-;

R_{25} is C_1 - C_8 alkyl optionally substituted by halogen, OH, or C_1 - C_4 -alkoxy or optionally interrupted by one or more -O-;

R_{26} is phenyl, optionally substituted by C_1 - C_4 alkyl or C_1 - C_4 alkyl- Y ; or is C_1 - C_8 alkyl optionally substituted by halogen, OH, OR_{25} , $COOR_{25}$, or C_1 - C_4 alkyl-COO-, or optionally interrupted by one or more -O-;

with the proviso that if R_3 is $CH_3C_6H_4SO_2$ -, R_6 , R_7 and R_8 are hydrogen and X is oxygen, then R_9 is not methyl or ethyl;

R_{10} is hydrogen, phenyl, C_1 - C_{12} alkyl which is unsubstituted or substituted by phenyl, OH, C_1 - C_{12} alkoxy, C_1 - C_{12} alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or by C_2 - C_6 -alkanoyl or R_{10} is C_2 - C_{12} alkyl interrupted by one or more -O-, said interrupted C_2 - C_{12} alkyl is unsubstituted or substituted by phenyl, OH, C_1 - C_{12} alkoxy, C_1 - C_{12} alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or by C_2 - C_6 alkanoyl;

R_{11} and R_{12} independently of one another are hydrogen, C_1 - C_{12} alkyl which is unsubstituted or substituted by OH, C_1 - C_4 alkoxy, C_1 - C_{12} alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or C_1 - C_6 alkanoyl; or R_{11} and R_{12} are C_2 - C_{12} alkyl interrupted by one or more -O-, said interrupted C_2 - C_{12} alkyl is unsubstituted or substituted by OH, C_1 - C_4 alkoxy, C_1 - C_{12} alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl and/or C_1 - C_6 alkanoyl; or R_{11} and R_{12} are phenyl, C_2 - C_6 alkanoyl, benzoyl, C_1 - C_6 alkylsulfonyl, phenylsulfonyl, (4-methylphenyl)sulfonyl, naphthylsulfonyl, anthracylsulfonyl or phenanthrylsulfonyl, or R_{11} and R_{12} , together with the nitrogen atom to which they are bonded, form a 5-, 6- or 7-membered ring which may be interrupted by -O- or by - NR_{10} -;

R_{13} is C_1 - C_{12} alkyl which is unsubstituted or substituted by OH and/or C_1 - C_4 alkoxy or is C_2 - C_{12} alkyl interrupted by one or more -O-, said interrupted C_2 - C_{12} alkyl is unsubstituted or substituted by OH and/or C_1 - C_4 alkoxy;

R_{14} and R_{15} independently of one another are C_1 - C_6 alkyl which is unsubstituted or substituted by halogen, or are phenyl which is unsubstituted or substituted by C_1 - C_4 alkyl or halogen;


R_{16} and R_{17} independently of one another have one of the meanings of R_{14} ; or R_{16} and R_{17} together are 1,2-phenylene or C_2 - C_6 alkylene which is unsubstituted or substituted by C_1 - C_4 alkyl or halogen;

R_{18} , R_{19} and R_{20} independently of each other are C_1 - C_6 alkyl, which is unsubstituted or substituted by halogen: or are phenyl which is unsubstituted or substituted by C_1 - C_4 alkyl or halogen, or R_{19} and R_{20} together are 2,2'-biphenylene or C_2 - C_6 alkylene which is unsubstituted or substituted by C_1 - C_4 alkyl or halogen.

11. A compound according to claim 10, wherein

R_3 is unsubstituted or fluorine-substituted C_1 - C_4 -alkylsulfonyl, unsubstituted or fluorine-

substituted phenylsulfonyl, C_1 - C_{12} -alkylphenylsulfonyl or a group $\begin{array}{c} Y_1 \\ || \\ -P-R_{14} \\ | \\ R_{15} \end{array}$,



R_6 , R_7 and R_8 independently of each other are hydrogen, $R_{26}Y$ -, phenyl optionally substituted by C_1 - C_4 alkyl or C_1 - C_4 alkyl- Y -; or R_6 , R_7 and R_8 are C_1 - C_8 alkyl optionally substituted by OH, OR_{25} , or $COOR_{25}$, or optionally interrupted by one or more -O-; or R_6 and R_7 together with the atoms to which they are bound form a 5- or 6-membered saturated or unsaturated ring which is unsubstituted or substituted by one or more C_1 - C_4 alkyl[†] and which ring optionally is interrupted by one or more Y or to which ring other rings are condensed;

Q is C_1 - C_8 -alkylene optionally interrupted by one or more -O-;

Y is -O- or -S-;

Y_1 , Y_2 and Y_3 are -O-;

X is -O- or - NR_9 -;

R_9 is cyclohexyl, phenyl, optionally substituted by C_1 - C_4 alkyl; or is C_1 - C_{12} alkyl, optionally substituted by OH, or OR_{25} , or optionally interrupted by one or more -O-;


R_{25} is C_1 - C_8 alkyl optionally substituted by OH or C_1 - C_4 -alkoxy or optionally interrupted by one or more -O-;

R_{26} is phenyl, optionally substituted by C_1 - C_4 alkyl or C_1 - C_4 alkyl- Y ; or is C_1 - C_8 alkyl optionally substituted by OH, OR_{25} , or $COOR_{25}$; or optionally interrupted by one or more -O-;

with the proviso that if R_3 is $\text{CH}_3\text{C}_6\text{H}_4\text{SO}_2^-$, R_6 , R_7 and R_8 are hydrogen and X is oxygen, then R_9 is not methyl or ethyl.

12. A compound according to claim 10, wherein

R_3 is $\text{C}_1\text{-C}_4$ -alkylsulfonyl, phenylsulfonyl, $\text{C}_1\text{-C}_{12}$ -alkylphenylsulfonyl or a group



R_6 , R_7 , R_8 independently of each other are hydrogen, $\text{C}_1\text{-C}_4$ alkyl, or $\text{R}_{26}\text{Y-}$,

or R_6 and R_7 together with the atoms to which they are bound form a 5- or 6-membered saturated or unsaturated ring which is unsubstituted or substituted by one or more $\text{C}_1\text{-C}_4$ alkyl and which ring optionally is interrupted by one or more Y or to which ring other rings are condensed;

Q is $\text{C}_1\text{-C}_8$ -alkylene optionally interrupted by one or more $-\text{O}-$;

X is $-\text{O}-$ or $-\text{NR}_9-$;

R_9 is $\text{C}_1\text{-C}_6$ alkyl, optionally interrupted by one or more $-\text{O}-$;

R_{26} is $\text{C}_1\text{-C}_4$ alkyl;

Y_1 and Y_2 are O ;

R_{14} and R_{15} independently of one another are phenyl or methylphenyl;

R_{16} and R_{17} independently of one another are $\text{C}_1\text{-C}_4$ -alkyl;

with the proviso that if R_3 is $\text{CH}_3\text{C}_6\text{H}_4\text{SO}_2^-$, R_6 , R_7 and R_8 are hydrogen and X is O , then R_9 is not methyl or ethyl.

13. A compound according to claim 10, namely

methyl α -(methylsulfonyloxyimino)-2-phenylacetate, propyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate, methylethyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate, butyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate, hexyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate, 2-methoxyethyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylphenyl)acetate, propyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylphenyl)acetate, butyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylphenyl)acetate, 2-methoxyethyl α -(4-methylphenylsulfonyloxyimino)-2-

(4-methylphenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-ethylphenyl)acetate, ethyl α -(4-butylphenylsulfonyloxyimino)-2-(4-methylphenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-fluorophenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methoxyphenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(3,4-dimethoxyphenyl)acetate, 2-methoxyethyl α -(4-methylphenylsulfonyloxyimino)-2-(3,4-dimethoxyphenyl)acetate, 2-methoxyethyl α -(methylsulfonyloxyimino)-2-(3,4-dimethoxyphenyl)acetate, methyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylthiophenyl)acetate, methyl α -(methylsulfonyloxyimino)-2-(4-methylthiophenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylthiophenyl)acetate, 2-methoxyethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-methylthiophenyl)acetate, 2-methoxyethyl α -(methylsulfonyloxyimino)-2-(4-methylthiophenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(3,4-butylthiophenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-dimethylaminophenyl)acetate, ethyl α -(4-methylphenylsulfonyloxyimino)-2-(thianthren-2-yl)acetate, methylsulfonyloxyimino-3,4-dimethoxyphenyl acetic acid 2-[2-(methylsulfonyloxyimino-3,4-dimethoxyphenyl-acetoxy)-ethoxy]-ethyl ester; N,N-diethyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetamide, N, N-diethyl α -(methylsulfonyloxyimino)-2-phenylacetamide, N, N-dibutyl α -(4-methylphenylsulfonyloxyimino)-2-phenylacetamide, N, N-diethyl α -(4-methylphenylsulfonyloxyimino)-2-(4-ethylphenyl)acetamide, methyl α -(diethoxyphosphoryloxyimino)-2-phenylacetate, ethyl α -(diethoxyphosphoryloxyimino)-2-phenylacetate, propyl α -(diethoxyphosphoryloxyimino)-2-phenylacetate; 2-methoxyethyl α -(diethoxyphosphoryloxyimino)-2-(3,4-dimethoxyphenyl)acetate, methyl α -(diethoxyphosphoryloxyimino)-2-(4-methylthiophenyl)acetate, ethyl α -(diethoxyphosphoryloxyimino)-2-(4-methylthiophenyl)acetate.

14. A process for the radical photopolymerization of compounds containing ethylenically unsaturated double bonds, which comprises irradiating a composition according to any one of claims 1 to 9 with electromagnetic radiation in the range from 190 to 600 nm, with e-beam radiation or with X-rays.

15. The use of a composition according to claim 1 for producing pigmented and nonpigmented paints and varnishes, powder coatings, printing inks, printing plates, adhesives, dental compositions, resist materials, including photoresists, color filter materials,

as composition for encapsulating electrical and electronic components, for producing magnetic recording materials, micromechanical parts, waveguides, optical switches, plating masks, etch masks, colour proofing systems, glass fibre cable coatings, screen printing stencils, for producing three-dimensional objects by means of stereolithography, and as image recording material, especially for holographic recordings, microelectronic circuits, decolorizing materials, decolorizing materials for image recording materials, for image recording materials using microcapsules.

16. A process according to claim 14 for producing pigmented and non-pigmented paints and varnishes, powder coatings, printing inks, printing plates, adhesives, dental compositions, composite compositions, resists, including photoresists, color filter materials, compositions for encapsulating electrical and electronic components, for producing magnetic recording materials, micromechanical parts, waveguides, optical switches, plating masks, etch masks, colour proofing systems, glass fibre cable coatings, screen printing stencils, for producing three-dimensional objects by means of microlithography, plating, stereolithography, for producing image recording materials, especially for holographic recordings, microelectronic circuits, decolorizing materials, decolorizing materials for image recording materials, for image recording materials using microcapsules.

17. Coated substrate which is coated on at least one surface with a composition according to claim 1.

18. Process for the production of relief images, in which a coated substrate according to claim 17 is subjected to imagewise exposure and then the unexposed portions are removed with a solvent.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 00/01404

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 G03F7/031 C07C381/00 C07C309/66 C07C309/73 C07D307/54

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 G03F C07C C07D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	WO 00 10972 A (CIBA SPECIALTY CHEMICALS HOLDING INC.) 2 March 2000 (2000-03-02) page 17, paragraph 3 -page 19 page 31, paragraph 5 claims ---	1-9, 14-18
E	DE 199 38 796 A (CIBA SPECIALTY CHEMICALS HOLDING INC.) 24 February 2000 (2000-02-24) page 3, line 12 - line 20 page 9, line 57 - line 68 page 11, line 44 - line 54 --- -/-	1-9, 14-18

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

1 August 2000

Date of mailing of the international search report

14 08. 2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Dupart, J.-M.

INTERNATIONAL SEARCH REPORT

International Application No

PC1/EP 00/01404

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	DE 199 28 742 A (CIBA SPECIALTY CHEMICALS HOLDING INC.) 30 December 1999 (1999-12-30) page 2, line 45 page 2, line 51 claims 1,8,11,14-18 ---	1-10, 14-18
P,X	WO 00 00869 A (CIBA SPECIALTY CHEMICALS HOLDING INC.) 6 January 2000 (2000-01-06) page 13, paragraph 2 page 18, paragraph 4 -page 19 page 27; claims ---	1-10, 14-18
A	WO 98 10335 A (CIBA SPECIALTY CHEMICALS HOLDING INC.) 12 March 1998 (1998-03-12) claims 19-21 -----	11-13

INTERNATIONAL SEARCH REPORT

In international application No.
PCT/EP 00/01404

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:

2. ☒ Claims Nos.: 1-12, 14-18
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210

3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.

2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.

3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:

4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box I.2

Claims Nos.: 1-12,14-18

Present claims 10-12 relate to an extremely large number of possible oxime compounds represented by the two Markush formulae V and VI. Support within the meaning of Article 6 PCT and/or disclosure within the meaning of Article 5 PCT is to be found, however, for only a very small proportion of the oxime compounds claimed. In the present case, the claims so lack support, and the application so lacks disclosure, that a meaningful search over the whole of the claimed scope is impossible. Consequently, the search has been carried out for those parts of the claims which appear to be supported and disclosed, namely those parts relating to the oxime compounds of present claim 13 and the compounds prepared:

- in the examples 1-34 (specific examples of compound of formula V wherein X is O and R3 is sulfonyl), - in the example 35 (specific example of compound of formula VI wherein X is O, R3 is methylsulfonyl and Q is CH2-CH2-O-CH2-CH2),
- in the examples 36-39 (specific examples of compound of formula V wherein X is N and R3 is sulfonyl), and
- in the examples 40-44 (specific examples of compound of formula V wherein X is O and R3 is phosphoryl) ..

Present claims 1-9 relate to an extremely large number of possible photopolymerizable compositions comprising an extremely large number of oxime ester compounds represented by six different Markush formulae. Support within the meaning of Article 6 PCT and/or disclosure within the meaning of Article 5 PCT is to be found, however, for only a very small proportion of the photopolymerizable compositions claimed. In the present case, the claims so lack support, and the application so lacks disclosure, that a meaningful search over the whole of the claimed scope is impossible. Consequently, the search has been carried out for those parts of the claims which appear to be supported and disclosed, namely those parts relating to the photopolymerizable compositions prepared in the examples 47-50.

This limitation of the search also applies to the processes for the radical polymerization of compounds containing ethylenically unsaturated double bonds (claims 14 and 16), which process makes use of the photopolymerizable compositions of claims 1-9, to the various uses of these compositions (claim 15), to the substrates coated with these compositions (claim 17), and to the process for the production of a relief image (claim 18), which process makes use of the latter coated substrate.

The applicant's attention is drawn to the fact that claims, or parts of claims, relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PC1/EP 00/01404

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 0010972 A	02-03-2000	AU 5373999 A	14-03-2000
DE 19938796 A	24-02-2000	AU 4452799 A	09-03-2000
		CN 1246655 A	08-03-2000
		FI 991731 A	18-02-2000
		FR 2782560 A	25-02-2000
		GB 2340494 A	23-02-2000
		JP 2000066385 A	03-03-2000
		NL 1012854 A	21-02-2000
		SE 9902913 A	19-02-2000
DE 19928742 A	30-12-1999	AU 3584499 A	13-01-2000
		FI 991407 A	27-12-1999
		FR 2781794 A	04-02-2000
		GB 2339571 A	02-02-2000
		JP 2000080068 A	21-03-2000
		NL 1012222 C	09-02-2000
		NL 1012222 A	04-01-2000
		SE 9902078 A	27-12-1999
WO 0000869 A	06-01-2000	AU 4773999 A	17-01-2000
WO 9810335 A	12-03-1998	AU 4455297 A	26-03-1998
		BR 9713311 A	01-02-2000
		CN 1228851 A	15-09-1999
		EP 0925529 A	30-06-1999